

(19) 世界知的所有権機関
国際事務局



(43) 国際公開日
2004 年 3 月 4 日 (04.03.2004)

PCT

(10) 国際公開番号
WO 2004/018587 A1

- (51) 国際特許分類: C09K 11/06 ケ浦市 上泉 1 2 8 0 番地 Chiba (JP). 井戸 元久 (IDO,Motohisa) [JP/JP]; 〒299-0205 千葉県 袖ケ浦市 上泉 1 2 8 0 番地 Chiba (JP). 舟橋 正和 (FUNA-HASHI,Masakazu) [JP/JP]; 〒299-0205 千葉県 袖ケ浦市 上泉 1 2 8 0 番地 Chiba (JP).
- (21) 国際出願番号: PCT/JP2003/010402
- (22) 国際出願日: 2003 年 8 月 18 日 (18.08.2003)
- (25) 国際出願の言語: 日本語 (74) 代理人: 大谷 保, 外(OHTANI,Tamotsu et al.); 〒105-0001 東京都 港区 虎ノ門 3 丁目 2 5 番 2 号 プリヂストン虎ノ門ビル 6 階 Tokyo (JP).
- (26) 国際公開の言語: 日本語 (81) 指定国 (国内): CN, IN, JP, KR, US.
- (30) 優先権データ: 特願2002-243545 2002 年 8 月 23 日 (23.08.2002) JP (84) 指定国 (広域): ヨーロッパ特許 (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).
- (71) 出願人 (米国を除く全ての指定国について): 出光興産株式会社 (IDEMITSU KOSAN CO., LTD.) [JP/JP]; 〒100-8321 東京都 千代田区 丸の内三丁目 1 番 1 号 Tokyo (JP). 添付公開書類:
— 国際調査報告書
- (72) 発明者; および 2 文字コード及び他の略語については、定期発行される各PCTガゼットの巻頭に掲載されている「コードと略語のガイダンスノート」を参照。
- (75) 発明者/出願人 (米国についてのみ): 池田 秀嗣 (IKEDA,Hidetugu) [JP/JP]; 〒299-0205 千葉県 袖

(54) Title: ORGANIC ELECTROLUMINESCENCE DEVICE AND ANTHRACENE DERIVATIVE

(54) 発明の名称: 有機エレクトロルミネッセンス素子及びアントラセン誘導体

(57) Abstract: An organic electroluminescence device comprising a negative electrode and a positive electrode and, interposed therebetween, one or two or more organic thin-film layers including at least a luminescent layer, wherein at least one of the organic thin-film layers contains an anthracene derivative of specified structure added alone or as a component of mixture; and an anthracene derivative of asymmetric specified structure. There are provided an organic electroluminescence device of high luminescence efficiency and long life and an anthracene derivative for realizing the same.

(57) 要約: 陰極と陽極間に少なくとも発光層を含む一層又は複数層からなる有機薄膜層が挟持されている有機エレクトロルミネッセンス素子において、該有機薄膜層の少なくとも 1 層が、特定構造のアントラセン誘導体を単独もしくは混合物の成分として含有する有機エレクトロルミネッセンス素子、並びに非対称型の特定構造を有するアントラセン誘導体であり、発光効率が高く、長寿命な有機エレクトロルミネッセンス素子及びそれを実現するアントラセン誘導体を提供する。

WO 2004/018587 A1

明 細 書

有機エレクトロルミネッセンス素子及びアントラセン誘導体

技術分野

本発明は、有機エレクトロルミネッセンス素子及びアントラセン誘導体に関し、さらに詳しくは、発光効率が高く長寿命な有機エレクトロルミネッセンス素子、それを実現するアントラセン誘導体に関するものである。

背景技術

有機エレクトロルミネッセンス素子（以下エレクトロルミネッセンスをELと略記することがある）は、電界を印加することより、陽極より注入された正孔と陰極より注入された電子の再結合エネルギーにより蛍光性物質が発光する原理を利用した自発光素子である。イーストマン・コダック社のC. W. Tangらによる積層型素子による低電圧駆動有機EL素子の報告（C. W. Tang, S. A. Vanslyke, アプライドフィジックスレターズ(Applied Physics Letters), 51巻、913頁、1987年等）がなされて以来、有機材料を構成材料とする有機EL素子に関する研究が盛んに行われている。Tangらは、トリス（8-ヒドロキシキノリノールアルミニウム）を発光層に、トリフェニルジアミン誘導体を正孔輸送層に用いている。積層構造の利点としては、発光層への正孔の注入効率を高めること、陰極より注入された電子をブロックして再結合により生成する励起子の生成効率を高めること、発光層内で生成した励起子を閉じ込めること等が挙げられる。この例のように有機EL素子の素子構造としては、正孔輸送（注入）層、電子輸送発光層の2層型、または正孔輸送（注入）層、発光層、電子輸送（注入）層の3層型等がよく知られている。こうした積層型構造素子では注入された正孔と電子の再結合効率を高めるため、素子構造や形成方法の工夫がなされている。

また、発光材料としてはトリス（８－キノリノラート）アルミニウム錯体等のキレート錯体、クマリン誘導体、テトラフェニルブタジエン誘導体、ビススチリルアアリーレン誘導体、オキサジアゾール誘導体等の発光材料が知られており、それらからは青色から赤色までの可視領域の発光が得られることが報告されており、カラー表示素子の実現が期待されている（例えば、特開平８－２３９６５５号公報、特開平７－１３８５６１号公報、特開平３－２００２８９号公報等）。

また、発光材料としてフェニルアントラセン誘導体を用いた素子が特開平８－０１２６００号公報に開示されている。このようなアントラセン誘導体は青色発光材料として用いられるが、素子寿命を伸ばすことが望まれていた。また、アントラセンの９，１０位にフルオランテン基を有する素子材料が特開２００１－２５７０７４号公報に開示されている。このようなアントラセン誘導体も青色発光材料として用いられるが、やはり素子寿命の改善が求められていた。さらに、特開２０００－１８２７７６号公報に種々のアントラセン誘導体を正孔輸送材料として用いることが開示されている。しかしながらその合成は実際にされておらず、発光材料としての評価は未だ成されていなかった。


発明の開示

本発明は、前記の課題を解決するためなされたもので、発光効率が高く、長寿命な有機ＥＬ素子及びそれを実現するアントラセン誘導体を提供することを目的とする。

本発明者らは、前記目的を達成するために、鋭意研究を重ねた結果、下記一般式（１）又は（２）で表される非対称型の特定構造を有するアントラセン構造を有する化合物を有機ＥＬ素子の発光材料として用いると、発光効率が高く、寿命が長い有機ＥＬ素子が得られることを見出し、本発明を完成するに至った。

すなわち、本発明は、陰極と陽極間に少なくとも発光層を含む一層又は複数層からなる有機薄膜層が挟持されている有機ＥＬ素子において、該有機薄膜層の少

なくとも1層が、下記一般式(1)又は(2)で表されるアントラセン誘導体を単独もしくは混合物の成分として含有する有機EL素子を提供するものである。




(式中、Arは置換もしくは無置換の核炭素数10～50の縮合芳香族基である。

Ar'は置換もしくは無置換の核炭素数6～50の芳香族基である。

Xは、置換もしくは無置換の核炭素数6～50の芳香族基、置換もしくは無置換の核原子数5～50の芳香族複素環基、置換もしくは無置換の炭素数1～50のアルキル基、置換もしくは無置換の炭素数1～50のアルコキシ基、置換もしくは無置換の炭素数6～50のアラルキル基、置換もしくは無置換の核原子数5～50のアリールオキシ基、置換もしくは無置換の核原子数5～50のアリールチオ基、置換もしくは無置換の炭素数1～50のアルコシカルボニル基、カルボキシ基、ハロゲン原子、シアノ基、ニトロ基、ヒドロキシ基である。


a、b及びcは、それぞれ0～4の整数である。

nは1～3の整数である。また、nが2以上の場合は、[]内の



は、同じでも異なってもよい。)

また、本発明は、下記一般式(2)で表されるアントラセン誘導体を提供するものである。




(式中、Arは置換もしくは無置換の核炭素数10～50の縮合芳香族基である。

Ar'は置換もしくは無置換の核炭素数6～50の芳香族基である。

Xは、置換もしくは無置換の核炭素数6～50の芳香族基、置換もしくは無置換の核原子数5～50の芳香族複素環基、置換もしくは無置換の炭素数1～50のアルキル基、置換もしくは無置換の炭素数1～50のアルコキシ基、置換もしくは無置換の炭素数6～50のアラルキル基、置換もしくは無置換の核原子数5～50のアリールオキシ基、置換もしくは無置換の核原子数5～50のアリールチオ基、置換もしくは無置換の炭素数1～50のアルコキシカルボニル基、カルボキシル基、ハロゲン原子、シアノ基、ニトロ基、ヒドロキシル基である。

a及びbは、それぞれ0～4の整数である。

nは1～3の整数である。また、nが2以上の場合は、[]内の



は、同じでも異なってもよい。)


発明を実施するための最良の形態

本発明の有機EL素子は、陰極と陽極間に少なくとも発光層を含む一層又は複数層からなる有機薄膜層が挟持されている有機EL素子において、該有機薄膜層の少なくとも1層が、上記一般式(1)で表されるアントラセン誘導体を単独もしくは混合物の成分として含有する。

一般式(1)において、Arは置換もしくは無置換の核炭素数10～50の縮合芳香族基である。

この縮合芳香族基としては、例えば、1-ナフチル基、2-ナフチル基、1-アントリル基、2-アントリル基、9-アントリル基、1-フェナントリル基、2-フェナントリル基、3-フェナントリル基、4-フェナントリル基、9-フェナントリル基、1-ナフタセニル基、2-ナフタセニル基、9-ナフタセニル基、1-ピレニル基、2-ピレニル基、4-ピレニル基、3-メチル-2-ナフチル基、4-メチル-1-ナフチル基、4-メチル-1-アントリル基等が挙げられる。

Arの縮合環芳香族基としては、下記の一般式



(Ar₁は、置換もしくは無置換の核炭素数6～50の芳香族基である。)から選ばれる基であると好ましい。

Ar₁としては、例えば、フェニル基、1-ナフチル基、2-ナフチル基、1-アントリル基、2-アントリル基、9-アントリル基、1-フェナントリル基、2-フェナントリル基、3-フェナントリル基、4-フェナントリル基、9-

フェナントリル基、1-ナフタセニル基、2-ナフタセニル基、9-ナフタセニル基、1-ピレニル基、2-ピレニル基、4-ピレニル基、2-ビフェニルイル基、3-ビフェニルイル基、4-ビフェニルイル基、p-ターフェニル-4-イル基、p-ターフェニル-3-イル基、p-ターフェニル-2-イル基、m-ターフェニル-4-イル基、m-ターフェニル-3-イル基、m-ターフェニル-2-イル基、o-トリル基、m-トリル基、p-トリル基、p-tert-ブチルフェニル基、p-(2-フェニルプロピル)フェニル基、3-メチル-2-ナフチル基、4-メチル-1-ナフチル基、4-メチル-1-アントリル基、4'-メチルビフェニルイル基、4''-tert-ブチル-p-ターフェニル-4-イル基等が挙げられる。

一般式(1)において、Ar'は、置換もしくは無置換の核炭素数6~50の芳香族基である。この芳香族基としては、フェニル基、1-ナフチル基、2-ナフチル基、1-アントリル基、2-アントリル基、9-アントリル基、1-フェナントリル基、2-フェナントリル基、3-フェナントリル基、4-フェナントリル基、9-フェナントリル基、1-ナフタセニル基、2-ナフタセニル基、9-ナフタセニル基、1-ピレニル基、2-ピレニル基、4-ピレニル基、2-ビフェニルイル基、3-ビフェニルイル基、4-ビフェニルイル基、p-ターフェニル-4-イル基、p-ターフェニル-3-イル基、p-ターフェニル-2-イル基、m-ターフェニル-4-イル基、m-ターフェニル-3-イル基、m-ターフェニル-2-イル基、o-トリル基、m-トリル基、p-トリル基、p-tert-ブチルフェニル基、p-(2-フェニルプロピル)フェニル基、3-メチル-2-ナフチル基、4-メチル-1-ナフチル基、4-メチル-1-アントリル基、4'-メチルビフェニルイル基、4''-tert-ブチル-p-ターフェニル-4-イル基等が挙げられる。

これらのうち、特に、1-ナフチル基、2-ナフチル基、9-フェナントリル基、1-ナフタセニル基、2-ナフタセニル基、9-ナフタセニル基、1-ピレ

ニル基、2-ピレニル基、4-ピレニル基、2-ビフェニルイル基、3-ビフェニルイル基、4-ビフェニルイル基、o-トリル基、m-トリル基、p-トリル基、p-tert-ブチルフェニル基等の核炭素数10以上の置換もしくは無置換の芳香族基が好ましい。

一般式(1)において、Xは、置換もしくは無置換の核炭素数6~50の芳香族基、置換もしくは無置換の核原子数5~50の芳香族複素環基、置換もしくは無置換の炭素数1~50のアルキル基、置換もしくは無置換の炭素数1~50のアルコキシ基、置換もしくは無置換の炭素数6~50のアラルキル基、置換もしくは無置換の核原子数5~50のアリールオキシ基、置換もしくは無置換の核原子数5~50のアリールチオ基、置換もしくは無置換の炭素数1~50のカルボキシル基、ハロゲン原子、シアノ基、ニトロ基、ヒドロキシル基である。

Xにおける置換もしくは無置換の芳香族基の例としては、フェニル基、1-ナフチル基、2-ナフチル基、1-アントリル基、2-アントリル基、9-アントリル基、1-フェナントリル基、2-フェナントリル基、3-フェナントリル基、4-フェナントリル基、9-フェナントリル基、1-ナフタセニル基、2-ナフタセニル基、9-ナフタセニル基、1-ピレニル基、2-ピレニル基、4-ピレニル基、2-ビフェニルイル基、3-ビフェニルイル基、4-ビフェニルイル基、p-ターフェニル-4-イル基、p-ターフェニル-3-イル基、p-ターフェニル-2-イル基、m-ターフェニル-4-イル基、m-ターフェニル-3-イル基、m-ターフェニル-2-イル基、o-トリル基、m-トリル基、p-トリル基、p-tert-ブチルフェニル基、p-(2-フェニルプロピル)フェニル基、3-メチル-2-ナフチル基、4-メチル-1-ナフチル基、4-メチル-1-アントリル基、4'-メチルビフェニルイル基、4"-tert-ブチル-p-ターフェニル-4-イル基等が挙げられる。

Xにおける置換もしくは無置換の芳香族複素環基の例としては、1-ピロリル基、2-ピロリル基、3-ピロリル基、ピラジニル基、2-ピリジニル基、3-

ピリジニル基、4-ピリジニル基、1-インドリル基、2-インドリル基、3-インドリル基、4-インドリル基、5-インドリル基、6-インドリル基、7-インドリル基、1-イソインドリル基、2-イソインドリル基、3-イソインドリル基、4-イソインドリル基、5-イソインドリル基、6-イソインドリル基、7-イソインドリル基、2-フリル基、3-フリル基、2-ベンゾフラニル基、3-ベンゾフラニル基、4-ベンゾフラニル基、5-ベンゾフラニル基、6-ベンゾフラニル基、7-ベンゾフラニル基、1-イソベンゾフラニル基、3-イソベンゾフラニル基、4-イソベンゾフラニル基、5-イソベンゾフラニル基、6-イソベンゾフラニル基、7-イソベンゾフラニル基、キノリル基、3-キノリル基、4-キノリル基、5-キノリル基、6-キノリル基、7-キノリル基、8-キノリル基、1-イソキノリル基、3-イソキノリル基、4-イソキノリル基、5-イソキノリル基、6-イソキノリル基、7-イソキノリル基、8-イソキノリル基、2-キノキサリニル基、5-キノキサリニル基、6-キノキサリニル基、1-カルバゾリル基、2-カルバゾリル基、3-カルバゾリル基、4-カルバゾリル基、9-カルバゾリル基、1-フェナンスリジニル基、2-フェナンスリジニル基、3-フェナンスリジニル基、4-フェナンスリジニル基、6-フェナンスリジニル基、7-フェナンスリジニル基、8-フェナンスリジニル基、9-フェナンスリジニル基、10-フェナンスリジニル基、1-アクリジニル基、2-アクリジニル基、3-アクリジニル基、4-アクリジニル基、9-アクリジニル基、1, 7-フェナンスロリン-2-イル基、1, 7-フェナンスロリン-3-イル基、1, 7-フェナンスロリン-4-イル基、1, 7-フェナンスロリン-5-イル基、1, 7-フェナンスロリン-6-イル基、1, 7-フェナンスロリン-8-イル基、1, 7-フェナンスロリン-9-イル基、1, 7-フェナンスロリン-10-イル基、1, 8-フェナンスロリン-2-イル基、1, 8-フェナンスロリン-3-イル基、1, 8-フェナンスロリン-4-イル基、1, 8-フェナンスロリン-5-イル基、1, 8-フェナンスロリン-6-イル基

、1, 8-フェナンスロリン-7-イル基、1, 8-フェナンスロリン-9-イル基、1, 8-フェナンスロリン-10-イル基、1, 9-フェナンスロリン-2-イル基、1, 9-フェナンスロリン-3-イル基、1, 9-フェナンスロリン-4-イル基、1, 9-フェナンスロリン-5-イル基、1, 9-フェナンスロリン-6-イル基、1, 9-フェナンスロリン-7-イル基、1, 9-フェナンスロリン-8-イル基、1, 9-フェナンスロリン-10-イル基、1, 10-フェナンスロリン-2-イル基、1, 10-フェナンスロリン-3-イル基、1, 10-フェナンスロリン-4-イル基、1, 10-フェナンスロリン-5-イル基、2, 9-フェナンスロリン-1-イル基、2, 9-フェナンスロリン-3-イル基、2, 9-フェナンスロリン-4-イル基、2, 9-フェナンスロリン-5-イル基、2, 9-フェナンスロリン-6-イル基、2, 9-フェナンスロリン-7-イル基、2, 9-フェナンスロリン-8-イル基、2, 9-フェナンスロリン-10-イル基、2, 8-フェナンスロリン-1-イル基、2, 8-フェナンスロリン-3-イル基、2, 8-フェナンスロリン-4-イル基、2, 8-フェナンスロリン-5-イル基、2, 8-フェナンスロリン-6-イル基、2, 8-フェナンスロリン-7-イル基、2, 8-フェナンスロリン-9-イル基、2, 8-フェナンスロリン-10-イル基、2, 7-フェナンスロリン-1-イル基、2, 7-フェナンスロリン-3-イル基、2, 7-フェナンスロリン-4-イル基、2, 7-フェナンスロリン-5-イル基、2, 7-フェナンスロリン-6-イル基、2, 7-フェナンスロリン-8-イル基、2, 7-フェナンスロリン-9-イル基、2, 7-フェナンスロリン-10-イル基、1-フェナジニル基、2-フェナジニル基、1-フェノチアジニル基、2-フェノチアジニル基、3-フェノチアジニル基、4-フェノチアジニル基、10-フェノチアジニル基、1-フェノキサジニル基、2-フェノキサジニル基、3-フェノキサジニル基、4-フェノキサジニル基、10-フェノキサジニル基、2-オキサゾリル基、4-オキサゾリル基、5-オキサゾリル基、2-オキサジアゾリル基、5

ーオキサジアゾリル基、3-フラザニル基、2-チエニル基、3-チエニル基、2-メチルピロール-1-イル基、2-メチルピロール-3-イル基、2-メチルピロール-4-イル基、2-メチルピロール-5-イル基、3-メチルピロール-1-イル基、3-メチルピロール-2-イル基、3-メチルピロール-4-イル基、3-メチルピロール-5-イル基、2-てーブチルピロール-4-イル基、3-(2-フェニルプロピル)ピロール-1-イル基、2-メチル-1-インドリル基、4-メチル-1-インドリル基、2-メチル-3-インドリル基、4-メチル-3-インドリル基、2-てーブチル1-インドリル基、4-てーブチル1-インドリル基、2-てーブチル3-インドリル基、4-てーブチル3-インドリル基等が挙げられる。

Xにおける置換もしくは無置換のアルキル基の例としては、メチル基、エチル基、プロピル基、イソプロピル基、n-ブチル基、s-ブチル基、イソブチル基、てーブチル基、n-ペンチル基、n-ヘキシル基、n-ヘブチル基、n-オクチル基、ヒドロキシメチル基、1-ヒドロキシエチル基、2-ヒドロキシエチル基、2-ヒドロキシイソブチル基、1, 2-ジヒドロキシエチル基、1, 3-ジヒドロキシイソプロピル基、2, 3-ジヒドロキシてーブチル基、1, 2, 3-トリヒドロキシプロピル基、クロロメチル基、1-クロロエチル基、2-クロロエチル基、2-クロロイソブチル基、1, 2-ジクロロエチル基、1, 3-ジクロロイソプロピル基、2, 3-ジクロロてーブチル基、1, 2, 3-トリクロロプロピル基、プロモメチル基、1-プロモエチル基、2-プロモエチル基、2-プロモイソブチル基、1, 2-ジプロモエチル基、1, 3-ジプロモイソプロピル基、2, 3-ジプロモてーブチル基、1, 2, 3-トリプロモプロピル基、ヨードメチル基、1-ヨードエチル基、2-ヨードエチル基、2-ヨードイソブチル基、1, 2-ジヨードエチル基、1, 3-ジヨードイソプロピル基、2, 3-ジヨードてーブチル基、1, 2, 3-トリヨードプロピル基、アミノメチル基、1-アミノエチル基、2-アミノエチル基、2-アミノイソブチル基、

1, 2-ジアミノエチル基、1, 3-ジアミノイソプロピル基、2, 3-ジアミノ-*tert*-ブチル基、1, 2, 3-トリアミノプロピル基、シアノメチル基、1-シアノエチル基、2-シアノエチル基、2-シアノイソブチル基、1, 2-ジシアノエチル基、1, 3-ジシアノイソプロピル基、2, 3-ジシアノ-*tert*-ブチル基、1, 2, 3-トリシアノプロピル基、ニトロメチル基、1-ニトロエチル基、2-ニトロエチル基、2-ニトロイソブチル基、1, 2-ジニトロエチル基、1, 3-ジニトロイソプロピル基、2, 3-ジニトロ-*tert*-ブチル基、1, 2, 3-トリニトロプロピル基、シクロプロピル基、シクロブチル基、シクロペンチル基、シクロヘキシル基、4-メチルシクロヘキシル基、1-アダマンチル基、2-アダマンチル基、1-ノルボルニル基、2-ノルボルニル基等が挙げられる。

置換又は無置換のアルコキシ基は、-OYで表される基であり、Yの例としては、メチル基、エチル基、プロピル基、イソプロピル基、*n*-ブチル基、*s*-ブチル基、イソブチル基、*tert*-ブチル基、*n*-ペンチル基、*n*-ヘキシル基、*n*-ヘプチル基、*n*-オクチル基、ヒドロキシメチル基、1-ヒドロキシエチル基、2-ヒドロキシエチル基、2-ヒドロキシイソブチル基、1, 2-ジヒドロキシエチル基、1, 3-ジヒドロキシイソプロピル基、2, 3-ジヒドロキシ-*tert*-ブチル基、1, 2, 3-トリヒドロキシプロピル基、クロロメチル基、1-クロロエチル基、2-クロロエチル基、2-クロロイソブチル基、1, 2-ジクロロエチル基、1, 3-ジクロロイソプロピル基、2, 3-ジクロロ-*tert*-ブチル基、1, 2, 3-トリクロロプロピル基、プロモメチル基、1-プロモエチル基、2-プロモエチル基、2-プロモイソブチル基、1, 2-ジプロモエチル基、1, 3-ジプロモイソプロピル基、2, 3-ジプロモ-*tert*-ブチル基、1, 2, 3-トリプロモプロピル基、ヨードメチル基、1-ヨードエチル基、2-ヨードエチル基、2-ヨードイソブチル基、1, 2-ジヨードエチル基、1, 3-ジヨードイソプロピル基、2, 3-ジヨード-*tert*-ブチル基、1, 2, 3-トリヨード

プロピル基、アミノメチル基、1-アミノエチル基、2-アミノエチル基、2-アミノイソブチル基、1, 2-ジアミノエチル基、1, 3-ジアミノイソプロピル基、2, 3-ジアミノ-*tert*-ブチル基、1, 2, 3-トリアミノプロピル基、シアノメチル基、1-シアノエチル基、2-シアノエチル基、2-シアノイソブチル基、1, 2-ジシアノエチル基、1, 3-ジシアノイソプロピル基、2, 3-ジシアノ-*tert*-ブチル基、1, 2, 3-トリシアノプロピル基、ニトロメチル基、1-ニトロエチル基、2-ニトロエチル基、2-ニトロイソブチル基、1, 2-ジニトロエチル基、1, 3-ジニトロイソプロピル基、2, 3-ジニトロ-*tert*-ブチル基、1, 2, 3-トリニトロプロピル基等が挙げられる。

置換又は無置換のアラルキル基の例としては、ベンジル基、1-フェニルエチル基、2-フェニルエチル基、1-フェニルイソプロピル基、2-フェニルイソプロピル基、フェニル-*tert*-ブチル基、 α -ナフチルメチル基、1- α -ナフチルエチル基、2- α -ナフチルエチル基、1- α -ナフチルイソプロピル基、2- α -ナフチルイソプロピル基、 β -ナフチルメチル基、1- β -ナフチルエチル基、2- β -ナフチルエチル基、1- β -ナフチルイソプロピル基、2- β -ナフチルイソプロピル基、1-ピロリルメチル基、2-(1-ピロリル)エチル基、*p*-メチルベンジル基、*m*-メチルベンジル基、*o*-メチルベンジル基、*p*-クロロベンジル基、*m*-クロロベンジル基、*o*-クロロベンジル基、*p*-ブロモベンジル基、*m*-ブロモベンジル基、*o*-ブロモベンジル基、*p*-ヨードベンジル基、*m*-ヨードベンジル基、*o*-ヨードベンジル基、*p*-ヒドロキシベンジル基、*m*-ヒドロキシベンジル基、*o*-ヒドロキシベンジル基、*p*-アミノベンジル基、*m*-アミノベンジル基、*o*-アミノベンジル基、*p*-ニトロベンジル基、*m*-ニトロベンジル基、*o*-ニトロベンジル基、*p*-シアノベンジル基、*m*-シアノベンジル基、*o*-シアノベンジル基、1-ヒドロキシ-2-フェニルイソプロピル基、1-クロロ-2-フェニルイソプロピル基等が挙げられる。

置換又は無置換のアリールオキシ基は、 $-OY'$ と表され、 Y' の例としては

フェニル基、1-ナフチル基、2-ナフチル基、1-アントリル基、2-アントリル基、9-アントリル基、1-フェナントリル基、2-フェナントリル基、3-フェナントリル基、4-フェナントリル基、9-フェナントリル基、1-ナフトセニル基、2-ナフトセニル基、9-ナフトセニル基、1-ビレニル基、2-ビレニル基、4-ビレニル基、2-ビフェニルイル基、3-ビフェニルイル基、4-ビフェニルイル基、p-ターフェニル-4-イル基、p-ターフェニル-3-イル基、p-ターフェニル-2-イル基、m-ターフェニル-4-イル基、m-ターフェニル-3-イル基、m-ターフェニル-2-イル基、o-トリル基、m-トリル基、p-トリル基、p-tert-ブチルフェニル基、p-(2-フェニルプロピル)フェニル基、3-メチル-2-ナフチル基、4-メチル-1-ナフチル基、4-メチル-1-アントリル基、4'-メチルビフェニルイル基、4"-tert-ブチル-p-ターフェニル-4-イル基、2-ピロリル基、3-ピロリル基、ピラジニル基、2-ピリジニル基、3-ピリジニル基、4-ピリジニル基、2-インドリル基、3-インドリル基、4-インドリル基、5-インドリル基、6-インドリル基、7-インドリル基、1-イソインドリル基、3-イソインドリル基、4-イソインドリル基、5-イソインドリル基、6-イソインドリル基、7-イソインドリル基、2-フリル基、3-フリル基、2-ベンゾフラニル基、3-ベンゾフラニル基、4-ベンゾフラニル基、5-ベンゾフラニル基、6-ベンゾフラニル基、7-ベンゾフラニル基、1-イソベンゾフラニル基、3-イソベンゾフラニル基、4-イソベンゾフラニル基、5-イソベンゾフラニル基、6-イソベンゾフラニル基、7-イソベンゾフラニル基、2-キノリル基、3-キノリル基、4-キノリル基、5-キノリル基、6-キノリル基、7-キノリル基、8-キノリル基、1-イソキノリル基、3-イソキノリル基、4-イソキノリル基、5-イソキノリル基、6-イソキノリル基、7-イソキノリル基、8-イソキノリル基、2-キノキサリニル基、5-キノキサリニル基、6-キノキサリニル基、1-カルバゾリル基、2-カルバゾリル基、3-カルバゾリル基、4-

カルバゾリル基、1-フェナンスリジニル基、2-フェナンスリジニル基、3-フェナンスリジニル基、4-フェナンスリジニル基、6-フェナンスリジニル基、7-フェナンスリジニル基、8-フェナンスリジニル基、9-フェナンスリジニル基、10-フェナンスリジニル基、1-アクリジニル基、2-アクリジニル基、3-アクリジニル基、4-アクリジニル基、9-アクリジニル基、1, 7-フェナンスロリン-2-イル基、1, 7-フェナンスロリン-3-イル基、1, 7-フェナンスロリン-4-イル基、1, 7-フェナンスロリン-5-イル基、1, 7-フェナンスロリン-6-イル基、1, 7-フェナンスロリン-8-イル基、1, 7-フェナンスロリン-9-イル基、1, 7-フェナンスロリン-10-イル基、1, 8-フェナンスロリン-2-イル基、1, 8-フェナンスロリン-3-イル基、1, 8-フェナンスロリン-4-イル基、1, 8-フェナンスロリン-5-イル基、1, 8-フェナンスロリン-6-イル基、1, 8-フェナンスロリン-7-イル基、1, 8-フェナンスロリン-9-イル基、1, 8-フェナンスロリン-10-イル基、1, 9-フェナンスロリン-2-イル基、1, 9-フェナンスロリン-3-イル基、1, 9-フェナンスロリン-4-イル基、1, 9-フェナンスロリン-5-イル基、1, 9-フェナンスロリン-6-イル基、1, 9-フェナンスロリン-7-イル基、1, 9-フェナンスロリン-8-イル基、1, 9-フェナンスロリン-10-イル基、1, 10-フェナンスロリン-2-イル基、1, 10-フェナンスロリン-3-イル基、1, 10-フェナンスロリン-4-イル基、1, 10-フェナンスロリン-5-イル基、2, 9-フェナンスロリン-1-イル基、2, 9-フェナンスロリン-3-イル基、2, 9-フェナンスロリン-4-イル基、2, 9-フェナンスロリン-5-イル基、2, 9-フェナンスロリン-6-イル基、2, 9-フェナンスロリン-7-イル基、2, 9-フェナンスロリン-8-イル基、2, 9-フェナンスロリン-10-イル基、2, 8-フェナンスロリン-1-イル基、2, 8-フェナンスロリン-3-イル基、2, 8-フェナンスロリン-4-イル基、2, 8-フェナンスロリ

ン-5-イル基、2, 8-フェナンスロリン-6-イル基、2, 8-フェナンスロリン-7-イル基、2, 8-フェナンスロリン-9-イル基、2, 8-フェナンスロリン-10-イル基、2, 7-フェナンスロリン-1-イル基、2, 7-フェナンスロリン-3-イル基、2, 7-フェナンスロリン-4-イル基、2, 7-フェナンスロリン-5-イル基、2, 7-フェナンスロリン-6-イル基、2, 7-フェナンスロリン-8-イル基、2, 7-フェナンスロリン-9-イル基、2, 7-フェナンスロリン-10-イル基、1-フェナジニル基、2-フェナジニル基、1-フェノチアジニル基、2-フェノチアジニル基、3-フェノチアジニル基、4-フェノチアジニル基、1-フェノキサジニル基、2-フェノキサジニル基、3-フェノキサジニル基、4-フェノキサジニル基、2-オキサゾリル基、4-オキサゾリル基、5-オキサゾリル基、2-オキサジアゾリル基、5-オキサジアゾリル基、3-フラザニル基、2-チエニル基、3-チエニル基、2-メチルピロール-1-イル基、2-メチルピロール-3-イル基、2-メチルピロール-4-イル基、2-メチルピロール-5-イル基、3-メチルピロール-1-イル基、3-メチルピロール-2-イル基、3-メチルピロール-4-イル基、3-メチルピロール-5-イル基、2-トープチルピロール-4-イル基、3-(2-フェニルプロピル)ピロール-1-イル基、2-メチル-1-インドリル基、4-メチル-1-インドリル基、2-メチル-3-インドリル基、4-メチル-3-インドリル基、2-トープチル-1-インドリル基、4-トープチル-1-インドリル基、2-トープチル-3-インドリル基、4-トープチル-3-インドリル基等が挙げられる。

置換又は無置換のアリールチオ基は、 $-SY''$ と表され、 Y'' の例としてはフェニル基、1-ナフチル基、2-ナフチル基、1-アントリル基、2-アントリル基、9-アントリル基、1-フェナントリル基、2-フェナントリル基、3-フェナントリル基、4-フェナントリル基、9-フェナントリル基、1-ナフタセニル基、2-ナフタセニル基、9-ナフタセニル基、1-ビレニル基、2-ビ

レニル基、4-ピレニル基、2-ビフェニルイル基、3-ビフェニルイル基、4-ビフェニルイル基、p-ターフェニル-4-イル基、p-ターフェニル-3-イル基、p-ターフェニル-2-イル基、m-ターフェニル-4-イル基、m-ターフェニル-3-イル基、m-ターフェニル-2-イル基、o-トリル基、m-トリル基、p-トリル基、p-tert-ブチルフェニル基、p-(2-フェニルプロピル)フェニル基、3-メチル-2-ナフチル基、4-メチル-1-ナフチル基、4-メチル-1-アントリル基、4'-メチルビフェニルイル基、4"-tert-ブチル-p-ターフェニル-4-イル基、2-ピロリル基、3-ピロリル基、ピラジニル基、2-ピリジニル基、3-ピリジニル基、4-ピリジニル基、2-インドリル基、3-インドリル基、4-インドリル基、5-インドリル基、6-インドリル基、7-インドリル基、1-イソインドリル基、3-イソインドリル基、4-イソインドリル基、5-イソインドリル基、6-イソインドリル基、7-イソインドリル基、2-フリル基、3-フリル基、2-ベンゾフラニル基、3-ベンゾフラニル基、4-ベンゾフラニル基、5-ベンゾフラニル基、6-ベンゾフラニル基、7-ベンゾフラニル基、1-イソベンゾフラニル基、3-イソベンゾフラニル基、4-イソベンゾフラニル基、5-イソベンゾフラニル基、6-イソベンゾフラニル基、7-イソベンゾフラニル基、2-キノリル基、3-キノリル基、4-キノリル基、5-キノリル基、6-キノリル基、7-キノリル基、8-キノリル基、1-イソキノリル基、3-イソキノリル基、4-イソキノリル基、5-イソキノリル基、6-イソキノリル基、7-イソキノリル基、8-イソキノリル基、2-キノキサリニル基、5-キノキサリニル基、6-キノキサリニル基、1-カルバゾリル基、2-カルバゾリル基、3-カルバゾリル基、4-カルバゾリル基、1-フェナンスリジニル基、2-フェナンスリジニル基、3-フェナンスリジニル基、4-フェナンスリジニル基、6-フェナンスリジニル基、7-フェナンスリジニル基、8-フェナンスリジニル基、9-フェナンスリジニル基、10-フェナンスリジニル基、1-アクリジニル基、2-アクリジニル基

、3-アクリジニル基、4-アクリジニル基、9-アクリジニル基、1, 7-フェナンスロリン-2-イル基、1, 7-フェナンスロリン-3-イル基、1, 7-フェナンスロリン-4-イル基、1, 7-フェナンスロリン-5-イル基、1, 7-フェナンスロリン-6-イル基、1, 7-フェナンスロリン-8-イル基、1, 7-フェナンスロリン-9-イル基、1, 7-フェナンスロリン-10-イル基、1, 8-フェナンスロリン-2-イル基、1, 8-フェナンスロリン-3-イル基、1, 8-フェナンスロリン-4-イル基、1, 8-フェナンスロリン-5-イル基、1, 8-フェナンスロリン-6-イル基、1, 8-フェナンスロリン-7-イル基、1, 8-フェナンスロリン-9-イル基、1, 8-フェナンスロリン-10-イル基、1, 9-フェナンスロリン-2-イル基、1, 9-フェナンスロリン-3-イル基、1, 9-フェナンスロリン-4-イル基、1, 9-フェナンスロリン-5-イル基、1, 9-フェナンスロリン-6-イル基、1, 9-フェナンスロリン-7-イル基、1, 9-フェナンスロリン-8-イル基、1, 9-フェナンスロリン-10-イル基、1, 10-フェナンスロリン-2-イル基、1, 10-フェナンスロリン-3-イル基、1, 10-フェナンスロリン-4-イル基、1, 10-フェナンスロリン-5-イル基、2, 9-フェナンスロリン-1-イル基、2, 9-フェナンスロリン-3-イル基、2, 9-フェナンスロリン-4-イル基、2, 9-フェナンスロリン-5-イル基、2, 9-フェナンスロリン-6-イル基、2, 9-フェナンスロリン-7-イル基、2, 9-フェナンスロリン-8-イル基、2, 9-フェナンスロリン-10-イル基、2, 8-フェナンスロリン-1-イル基、2, 8-フェナンスロリン-3-イル基、2, 8-フェナンスロリン-4-イル基、2, 8-フェナンスロリン-5-イル基、2, 8-フェナンスロリン-6-イル基、2, 8-フェナンスロリン-7-イル基、2, 8-フェナンスロリン-9-イル基、2, 8-フェナンスロリン-10-イル基、2, 7-フェナンスロリン-1-イル基、2, 7-フェナンスロリン-3-イル基、2, 7-フェナンスロリン-4-イル基、2, 7-

ーフェナンスロリンー5-イル基、2, 7-フェナンスロリンー6-イル基、2, 7-フェナンスロリンー8-イル基、2, 7-フェナンスロリンー9-イル基、2, 7-フェナンスロリンー10-イル基、1-フェナジニル基、2-フェナジニル基、1-フェノチアジニル基、2-フェノチアジニル基、3-フェノチアジニル基、4-フェノチアジニル基、1-フェノキサジニル基、2-フェノキサジニル基、3-フェノキサジニル基、4-フェノキサジニル基、2-オキサゾリル基、4-オキサゾリル基、5-オキサゾリル基、2-オキサジアゾリル基、5-オキサジアゾリル基、3-フラザニル基、2-チエニル基、3-チエニル基、2-メチルピロールー1-イル基、2-メチルピロールー3-イル基、2-メチルピロールー4-イル基、2-メチルピロールー5-イル基、3-メチルピロールー1-イル基、3-メチルピロールー2-イル基、3-メチルピロールー4-イル基、3-メチルピロールー5-イル基、2-ト-ブチルピロールー4-イル基、3-(2-フェニルプロピル)ピロールー1-イル基、2-メチル-1-インドリル基、4-メチル-1-インドリル基、2-メチル-3-インドリル基、4-メチル-3-インドリル基、2-ト-ブチル1-インドリル基、4-ト-ブチル1-インドリル基、2-ト-ブチル3-インドリル基、4-ト-ブチル3-インドリル基等が挙げられる。

置換又は無置換のアルコキシカルボニル基は-COOZと表され、Zの例としてはメチル基、エチル基、プロピル基、イソプロピル基、n-ブチル基、s-ブチル基、イソブチル基、t-ブチル基、n-ペンチル基、n-ヘキシル基、n-ヘプチル基、n-オクチル基、ヒドロキシメチル基、1-ヒドロキシエチル基、2-ヒドロキシエチル基、2-ヒドロキシイソブチル基、1, 2-ジヒドロキシエチル基、1, 3-ジヒドロキシイソプロピル基、2, 3-ジヒドロキシト-ブチル基、1, 2, 3-トリヒドロキシプロピル基、クロロメチル基、1-クロロエチル基、2-クロロエチル基、2-クロロイソブチル基、1, 2-ジクロロエチル基、1, 3-ジクロロイソプロピル基、2, 3-ジクロロト-ブチル基

、1, 2, 3-トリクロロプロピル基、ブロモメチル基、1-ブロモエチル基、2-ブロモエチル基、2-ブロモイソブチル基、1, 2-ジブロモエチル基、1, 3-ジブロモイソプロピル基、2, 3-ジブロモ-*tert*-ブチル基、1, 2, 3-トリブロモプロピル基、ヨードメチル基、1-ヨードエチル基、2-ヨードエチル基、2-ヨードイソブチル基、1, 2-ジヨードエチル基、1, 3-ジヨードイソプロピル基、2, 3-ジヨード-*tert*-ブチル基、1, 2, 3-トリヨードプロピル基、アミノメチル基、1-アミノエチル基、2-アミノエチル基、2-アミノイソブチル基、1, 2-ジアミノエチル基、1, 3-ジアミノイソプロピル基、2, 3-ジアミノ-*tert*-ブチル基、1, 2, 3-トリアミノプロピル基、シアノメチル基、1-シアノエチル基、2-シアノエチル基、2-シアノイソブチル基、1, 2-ジシアノエチル基、1, 3-ジシアノイソプロピル基、2, 3-ジシアノ-*tert*-ブチル基、1, 2, 3-トリアシアノプロピル基、ニトロメチル基、1-ニトロエチル基、2-ニトロエチル基、2-ニトロイソブチル基、1, 2-ジニトロエチル基、1, 3-ジニトロイソプロピル基、2, 3-ジニトロ-*tert*-ブチル基、1, 2, 3-トリニトロプロピル基等が挙げられる。

また、環を形成する2価基の例としては、テトラメチレン基、ペンタメチレン基、ヘキサメチレン基、ジフェニルメタン-2, 2'-ジイル基、ジフェニルエタン-3, 3'-ジイル基、ジフェニルプロパン-4, 4'-ジイル基等が挙げられる。

ハロゲン原子としては、フッ素、塩素、臭素、ヨウ素等が挙げられる。

一般式(1)において、a、b及びcは、それぞれ0～4の整数であり、0～1であると好ましい。


nは1～3の整数である。またnが2以上の場合は、[]内の基は、同じでも異なってもよい。


前記Ar、Ar'及びXが示す基における置換基としては、ハロゲン原子、ヒドロキシル基、ニトロ基、シアノ基、アルキル基、アリール基、シクロアルキル


基、アルコキシ基、芳香族複素環基、アラルキル基、アリーロキシ基、アリー
ルチオ基、アルコシカルボニル基、又はカルボキシル基などが挙げられる。


本発明の一般式(1)で表されるアントラセン誘導体の具体例を以下に示すが、
これら例示化合物に限定されるものではない。なお、Meはメチル基、Buは
ブチル基を示す。


また、一般式(1)で表されるアントラセン誘導体において、Ar及びAr'
が共にナフチル基であり、かつ $a=b=c=0$ のものが最も好ましい。














AN51




AN52




AN53




AN54




AN55




AN56




AN57




AN58



AN59



AN60



本発明の上記一般式(2)で表されるアントラセン誘導体は、上記一般式(1)に含まれるもののうち、新規な化合物である。

一般式(2)において、Arは置換もしくは無置換の核炭素数10～50の縮合芳香族基である。

一般式(2)において、Ar'は置換もしくは無置換の核炭素数6～50の芳香族基である。

一般式(2)において、Xは、置換もしくは無置換の核炭素数6～50の芳香族基、置換もしくは無置換の核原子数5～50の芳香族複素環基、置換もしくは無置換の炭素数1～50のアルキル基、置換もしくは無置換の炭素数1～50のアルコキシ基、置換もしくは無置換の炭素数6～50のアラルキル基、置換もしくは無置換の核原子数5～50のアリールオキシ基、置換もしくは無置換の核原子数5～50のアリールチオ基、置換もしくは無置換の炭素数1～50のアルコキシカルボニル基、カルボキシル基、ハロゲン原子、シアノ基、ニトロ基、ヒドロキシル基である。

これら、Ar、Ar'及びXが示す各基の具体例は、前記一般式(1)にて例示したものと同様である。

また、前記Ar、Ar'及びXが示す基における置換基としては、ハロゲン原子、ヒドロキシル基、ニトロ基、シアノ基、アルキル基、アリール基、シクロアルキル基、アルコキシ基、芳香族複素環基、アラルキル基、アリールオキシ基、アリールチオ基、アルコキシカルボニル基、又はカルボキシル基などが挙げられる。

一般式(2)において、a及びbは、それぞれ0～4の整数であり、0～1であると好ましい。

nは1～3の整数である。またnが2以上の場合は、[]内の基は、同じでも異なってもよい。

本発明の一般式(2)で表されるアントラセン誘導体の具体例としては、前記

一般式(1)の具体例のうち、(AN1)～(AN4)、(AN7)～(AN14)、(AN17)～(AN24)、(AN27)～(AN36)、(AN39)～(AN43)及び(AN46)～(AN48)が挙げられるが、それらの例示化合物に限定されるものではない。

また、本発明の一般式(2)で表されるアントラセン誘導体は、有機EL素子用材料として用いられると好ましい。

本発明の有機EL素子に用いる一般式(1)もしくは(2)のアントラセン誘導体は、市販のアリールボロン酸もしくは既知の方法により合成したアリールボロン酸又はその誘導体とハロゲン化アントラセン誘導体を出発原料として、鈴木カップリング反応・ハロゲン化反応・ホウ酸化反応を適宜組み合わせて、合成することができる。以下にその合成スキームを示す。

 $A_r, A_{r'} X, a \sim c, n$ は前記と同じ

R^1, R^2 : 水酸基または置換基を有しても良いアルコキシ基
 R^1, R^2 は結合して環を形成しても良い

鈴木カップリング反応は、これまでに数多くの報告 (Chem. Rev., Vol. 95, No. 7, 2457 (1995) 等) がなされており、これらに記載の反応条件で実施することができる。

反応は、通常、常圧下、窒素、アルゴン、ヘリウム等の不活性雰囲気下で実施されるが、必要に応じて加圧条件下に実施することも出来る。反応温度は 15 ~ 300℃ の範囲であるが、特に好ましくは 30 ~ 200℃ である。

反応溶媒としては、水、ベンゼン、トルエン、キシレン等の芳香族炭化水素類、1, 2-ジメトキシエタン、ジエチルエーテル、メチル-tert-ブチルエーテル、テトラヒドロフラン、ジオキサン等のエーテル類、ペンタン、ヘキサン、ヘプタン、オクタン、シクロヘキサン等の飽和炭化水素類、ジクロロメタン、クロロホルム、四塩化炭素、1, 2-ジクロロエタン、1, 1, 1-トリクロロエタンなどのハロゲン類、アセトニトリル、ベンゾニトリル等のニトリル類、酢酸エチル、酢酸メチル、酢酸ブチル等のエステル類、N, N-ジメチルホルムアミド、N, N-ジメチルアセトアミド、N-メチルピロリドン等のアミド類などを単一又は混合して使用することができる。これらの中で、好ましくは、トルエン、1, 2-ジメトキシエタン、ジオキサン、水である。溶媒の使用量はアリールボロン酸又はその誘導体に対して、通常 3 ~ 50 重量倍、好ましくは 4 ~ 20 重量倍である。

反応に用いる塩基としては、例えば、炭酸ナトリウム、炭酸カリウム、水酸化ナトリウム水酸化カリウム、炭酸水素ナトリウム、炭酸水素カリウム、炭酸マグネシウム、炭酸リチウム、ふっ化カリウム、フッ化セシウム、塩化セシウム、臭化セシウム、炭酸セシウム、リン酸カリウム、メトキシナトリウム、tert-ブトキシカリウム、tert-ブトキシナトリウム、tert-ブトキシリチウム等が挙げられ、好ましくは炭酸ナトリウムである。これらの塩基の使用量は、アリールボロン酸又はその誘導体に対して、通常 0.7 ~ 1.0 モル当量、好ましくは 0.9 ~ 6 モル当量である。

反応に用いる触媒としては、例えば、テトラキス（トリフェニルホスフィン）パラジウム、ジクロロビス（トリフェニルホスフィン）パラジウム、ジクロロ[ビス（ジフェニルホスフィノ）エタン]パラジウム、ジクロロ[ビス（ジフェニルホスフィノ）プロパン]パラジウム、ジクロロ[ビス（ジフェニルホスフィノ）ブタン]パラジウム、ジクロロ[ビス（ジフェニルホスフィノ）フェロセン]パラジウム等のパラジウム触媒、テトラキス（トリフェニルホスフィン）ニッケル、ジクロロビス（トリフェニルホスフィン）ニッケル、ジクロロ[ビス（ジフェニルホスフィノ）エタン]ニッケル、ジクロロ[ビス（ジフェニルホスフィノ）プロパン]ニッケル、ジクロロ[ビス（ジフェニルホスフィノ）ブタン]ニッケル、ジクロロ[ビス（ジフェニルホスフィノ）フェロセン]ニッケル等のニッケル触媒等が挙げられ、好ましくはテトラキス（トリフェニルホスフィン）パラジウムである。これらの触媒の使用量はハロゲン化アントラセン誘導体に対して、通常0.001～1モル当量、好ましくは0.01～0.1モル当量である。

ハロゲン化アントラセン誘導体のハロゲンとしては、例えば、ヨウ素原子、臭素原子、塩素原子等が挙げられ、好ましくはヨウ素原子、臭素原子である。

ハロゲン化反応におけるハロゲン化剤は特に限定されるものではないが、例えば、N-ハロゲン化コハク酸イミドが好適に用いられる。ハロゲン化剤の使用量はアントラセン誘導体に対し、通常0.8～10モル当量、好ましくは1～5モル当量である。

反応は、通常、窒素、アルゴン、ヘリウム等の不活性雰囲気下、不活性溶媒中で実施される。使用される不活性溶媒としては、例えば、N,N-ジメチルホルムアミド、N,N-ジメチルアセトアミド、N-メチルピロリドン、ジメチルスルホキシド、四塩化炭素、クロロベンゼン、ジクロロベンゼン、ニトロベンゼン、トルエン、キシレンメチルセロソルブ、エチルセロソルブ、水等が挙げられ、好ましくはN,N-ジメチルホルムアミド、N-メチルピロリドンである。溶媒

の使用量はアントラセン誘導体に対し、通常 3 ～ 50 重量倍、好ましくは 5 ～ 20 重量倍である。反応温度は、通常 0℃ ～ 200℃ で実施され、好ましくは 20℃ ～ 120℃ である。

ホウ酸化反応は、既知の方法（日本化学会編・実験化学講座第 4 版 24 巻 61 ～ 90 頁や J. Org. Chem., Vol. 60, 7508 (1995) 等）により実施することが可能である。例えば、ハロゲン化アントラセン誘導体のリチオ化もしくはグリニャール反応を経由する反応の場合、通常、窒素、アルゴン、ヘリウム等の不活性雰囲気下で実施され、反応溶媒としては不活性溶媒が用いられる。例えば、ペンタン、ヘキサン、ヘプタン、オクタン、シクロヘキサン等の飽和炭化水素類、1, 2-ジメトキシエタン、ジエチルエーテル、メチル-tert-ブチルエーテル、テトラヒドロフラン、ジオキサン等のエーテル類、ベンゼン、トルエン、キシレン等の芳香族炭化水素類を単一もしくは混合溶媒として用いることができ、好ましくはジエチルエーテル、トルエンである。溶媒の使用量は、ハロゲン化アントラセン誘導体に対し通常 3 ～ 50 重量倍、好ましくは 4 ～ 20 重量倍である。

リチオ化剤としては、例えば、n-ブチルリチウム、tert-ブチルリチウム、フェニルリチウム、メチルリチウム等のアルキル金属試薬、リチウムジイソプロピルアミド、リチウムビストリメチルシリルアミド等のアミド塩基を用いることができ、好ましくは n-ブチルリチウムである。また、グリニャール試薬は、ハロゲン化アントラセン誘導体と金属マグネシウムの反応により調製することができる。ホウ酸化剤であるホウ酸トリアルキルとしては、例えば、ホウ酸トリメチル、ホウ酸トリエチル、ホウ酸トリイソプロピル、ホウ酸トリブチル等を使用することができ、好ましくはホウ酸トリメチル、ホウ酸トリイソプロピルである。


リチオ化剤及び金属マグネシウムの使用量は、それぞれハロゲン化アントラセン誘導体に対し、通常 1 ～ 10 モル当量、好ましくは 1 ～ 2 モル当量であり、ホウ酸トリアルキルの使用量は、ハロゲン化アントラセン誘導体に対し、通常 1 ～ 10 モル当量、好ましくは 1 ～ 5 モル当量である。反応温度は、通常 -100 ～

50℃、好ましくは-75～10℃である。

本発明の有機EL素子は、前記発光層が、一般式(1)又は(2)で表されるアントラセン誘導体を主成分として含有すると好ましい。

また、本発明の有機EL素子は、前記発光層が、さらにアリールアミン化合物及び／又はスチリルアミン化合物を含有すると好ましい。


スチリルアミン化合物としては、下記一般式(A)で表されるものが好ましい。



(式中、Ar₂は、フェニル基、ビフェニル基、ターフェニル基、スチルベン基、ジスチリルアリール基から選ばれる基であり、Ar₃及びAr₄は、それぞれ水素原子又は炭素数が6～20の芳香族基であり、Ar₂、Ar₃及びAr₄は置換されいてもよい。pは1～4の整数である。さらに好ましくはAr₃又はAr₄の少なくとも一方はスチリル基で置換されている。)

ここで、炭素数が6～20の芳香族基としては、フェニル基、ナフチル基、アントラニル基、フェナンスリル基、ターフェニル基等が挙げられる。

アリールアミン化合物としては、下記一般式(B)で表されるものが好ましい。



(式中、 $Ar_5 \sim Ar_7$ は、置換もしくは無置換の核炭素数 5 ～ 40 のアリール基である。 q は 1 ～ 4 の整数である。)

ここで、核炭素数が 5 ～ 40 のアリール基としては、例えば、フェニル基、ナフチル基、アントラニル基、フェナンスリル基、ピレニル基、コロニル基、ビフェニル基、ターフェニル基、ピローリル基、フラニル基、チオフェニル基、ベンゾチオフェニル基、オキサジアゾリル基、ジフェニルアントラニル基、インドリル基、カルバゾリル基、ピリジル基、ベンゾキノリル基、フルオランテニル基、アセナフトフルオランテニル基、スチルベン基等が挙げられる。なお、このアリール基の好ましい置換基としては、炭素数 1 ～ 6 のアルキル基 (エチル基、メチル基、*i*-プロピル基、*n*-プロピル基、*s*-ブチル基、*t*-ブチル基、ペンチル基、ヘキシル基、シクロペンチル基、シクロヘキシル基等)、炭素数 1 ～ 6 のアルコキシ基 (エトキシ基、メトキシ基、*i*-プロポキシ基、*n*-プロポキシ基、*s*-ブトキシ基、*t*-ブトキシ基、ペントキシ基、ヘキシルオキシ基、シクロペントキシ基、シクロヘキシルオキシ基等)、核原子数 5 ～ 40 のアリール基、核原子数 5 ～ 40 のアリール基で置換されたアミノ基、核原子数 5 ～ 40 のアリール基を有するエステル基、炭素数 1 ～ 6 のアルキル基を有するエステル基、シアノ基、ニトロ基、ハロゲン原子等が挙げられる。

以下、本発明の有機 EL 素子の素子構成について説明する。

本発明の有機 EL 素子の代表的な素子構成としては、

- (1) 陽極／発光層／陰極
- (2) 陽極／正孔注入層／発光層／陰極
- (3) 陽極／発光層／電子注入層／陰極
- (4) 陽極／正孔注入層／発光層／電子注入層／陰極
- (5) 陽極／有機半導体層／発光層／陰極
- (6) 陽極／有機半導体層／電子障壁層／発光層／陰極
- (7) 陽極／有機半導体層／発光層／付着改善層／陰極

- (8) 陽極／正孔注入層／正孔輸送層／発光層／電子注入層／陰極
- (9) 陽極／絶縁層／発光層／絶縁層／陰極
- (10) 陽極／無機半導体層／絶縁層／発光層／絶縁層／陰極
- (11) 陽極／有機半導体層／絶縁層／発光層／絶縁層／陰極
- (12) 陽極／絶縁層／正孔注入層／正孔輸送層／発光層／絶縁層／陰極
- (13) 陽極／絶縁層／正孔注入層／正孔輸送層／発光層／電子注入層／陰極

などの構造を挙げることができる。

これらの中で通常(8)の構成が好ましく用いられるが、もちろんこれらに限定されるものではない。

この有機EL素子は、通常透光性の基板上に作製する。この透光性基板は有機EL素子を支持する基板であり、その透光性については、400～700nmの可視領域の光の透過率が50%以上であるものが望ましく、さらに平滑な基板を用いるのが好ましい。

このような透光性基板としては、例えば、ガラス板、合成樹脂板などが好適に用いられる。ガラス板としては、特にソーダ石灰ガラス、バリウム・ストロンチウム含有ガラス、鉛ガラス、アルミノケイ酸ガラス、ホウケイ酸ガラス、バリウムホウケイ酸ガラス、石英などで成形された板が挙げられる。また、合成樹脂板としては、ポリカーボネート樹脂、アクリル樹脂、ポリエチレンテレフタレート樹脂、ポリエーテルサルファイド樹脂、ポリサルフォン樹脂などの板が挙げられる。

次に、上記の陽極としては、仕事関数の大きい(4eV以上)金属、合金、電気伝導性化合物又はこれらの混合物を電極物質とするものが好ましく用いられる。このような電極物質の具体例としては、Auなどの金属、CuI、ITO(インジウムチンオキシド)、 SnO_2 、 ZnO 、 In-Zn-O などの導電性材料が挙げられる。この陽極を形成するには、これらの電極物質を、蒸着法やスパッタリング法等の方法で薄膜を形成させることができる。この陽極は、上記発光層

からの発光を陽極から取り出す場合、陽極の発光に対する透過率が10%より大きくなるような特性を有していることが望ましい。また、陽極のシート抵抗は、数百 Ω/\square 以下のものが好ましい。さらに、陽極の膜厚は、材料にもよるが通常10nm~1 μ m、好ましくは10~200nmの範囲で選択される。

次に、陰極としては、仕事関数の小さい(4eV以下)金属、合金、電気伝導性化合物及びこれらの混合物を電極物質とするものが用いられる。このような電極物質の具体例としては、ナトリウム、ナトリウム-カリウム合金、マグネシウム、リチウム、マグネシウム・銀合金、アルミニウム/酸化アルミニウム、Al/Li₂O, Al/LiO₂, Al/LiF, アルミニウム・リチウム合金、インジウム、希土類金属などが挙げられる。

この陰極はこれらの電極物質を蒸着やスパッタリング等の方法により薄膜を形成させることにより、作製することができる。

ここで、発光層からの発光を陰極から取り出す場合、陰極の発光に対する透過率は10%より大きくすることが好ましい。また、陰極としてのシート抵抗は数百 Ω/\square 以下が好ましく、さらに、膜厚は通常10nm~1 μ m、好ましくは50~200nmである。

本発明の有機EL素子においては、このようにして作製された一対の電極の少なくとも一方の表面に、カルコゲナイド層、ハロゲン化金属層又は金属酸化物層(以下、これらを表面層ということがある。)を配置するのが好ましい。具体的には、発光層側の陽極表面にケイ素やアルミニウムなどの金属のカルコゲナイド(酸化物を含む)層を、また、発光層側の陰極表面にハロゲン化金属層又は金属酸化物層を配置するのがよい。これにより、駆動の安定化を図ることができる。

上記カルコゲナイドとしては、例えばSiO_x (1 \leq X \leq 2), AlO_x (1 \leq X \leq 1.5), SiON, SiAlONなどが好ましく挙げられ、ハロゲン化金属としては、例えばLiF, MgF₂, CaF₂, フッ化希土類金属などが好ましく挙げられ、金属酸化物としては、例えばCs₂O, Li₂O, MgO, Sr

O, BaO, CaOなどが好ましく挙げられる。

さらに、本発明の有機EL素子においては、このようにして作製された一対の電極の少なくとも一方の表面に電子伝達化合物と還元性ドーパントの混合領域又は正孔伝達化合物と酸化性ドーパントの混合領域を配置するのも好ましい。このようにすると、電子伝達化合物が還元され、アニオンとなり混合領域がより発光層に電子を注入、伝達しやすくなる。また、正孔伝達化合物は酸化され、カチオンとなり混合領域がより発光層に正孔を注入、伝達しやすくなる。好ましい酸化性ドーパントとしては、各種ルイス酸やアクセプター化合物がある。好ましい還元性ドーパントとしては、アルカリ金属、アルカリ金属化合物、アルカリ土類金属、希土類金属及びこれらの化合物がある。

本発明の有機EL素子においては、発光層は、

- ①注入機能；電界印加時に陽極又は正孔注入層より正孔を注入することができ、陰極又は電子注入層より電子を注入することができる機能
- ②輸送機能；注入した電荷（電子と正孔）を電界の力で移動させる機能
- ③発光機能；電子と正孔の再結合の場を提供し、これを発光につなげる機能を有する。

この発光層を形成する方法としては、例えば蒸着法、スピンコート法、LB法等の公知の方法を適用することができる。発光層は、特に分子堆積膜であることが好ましい。ここで分子堆積膜とは、気相状態の材料化合物から沈着され形成された薄膜や、溶液状態または液相状態の材料化合物から固体化され形成された膜のことであり、通常この分子堆積膜は、LB法により形成された薄膜（分子累積膜）とは凝集構造、高次構造の相違や、それに起因する機能的な相違により区分することができる。

また特開昭57-51781号公報に開示されているように、樹脂等の結着剤と材料化合物とを溶剤に溶かして溶液とした後、これをスピンコート法等により薄膜化することによっても、発光層を形成することができる。

本発明においては、本発明の目的が損なわれない範囲で、所望により、発光層に、本発明の発光材料以外の他の公知の発光材料を含有させてもよく、また、本発明の発光材料を含む発光層に、他の公知の発光材料を含む発光層を積層してもよい。

次に、正孔注入・輸送層は、発光層への正孔注入を助け、発光領域まで輸送する層であって、正孔移動度が大きく、イオン化エネルギーが通常 5.5 eV 以下と小さい。このような正孔注入・輸送層としてはより低い電界強度で正孔を発光層に輸送する材料が好ましく、さらに正孔の移動度が、例えば $10^4 \sim 10^6 \text{ V/cm}$ の電界印加時に、少なくとも $10^{-6} \text{ cm}^2/\text{V} \cdot \text{秒}$ であるものが好ましい。このような材料としては、従来、光導伝材料において正孔の電荷輸送材料として慣用されているものや、有機EL素子の正孔注入層に使用されている公知のものの中から任意のものを選択して用いることができる。

そして、この正孔注入・輸送層を形成するには、正孔注入・輸送材料を、例えば真空蒸着法、スピンコート法、キャスト法、LB法等の公知の方法により薄膜化すればよい。この場合、正孔注入・輸送層としての膜厚は、特に制限はないが、通常は $5 \text{ nm} \sim 5 \mu\text{m}$ である。

次に、電子注入層・輸送層は、発光層への電子の注入を助け、発光領域まで輸送する層であって、電子移動度が大きく、また付着改善層は、この電子注入層の中で特に陰極との付着が良い材料からなる層である。電子注入層に用いられる材料としては、8-ヒドロキシキノリンまたはその誘導体の金属錯体が好適である。上記8-ヒドロキシキノリンまたはその誘導体の金属錯体の具体例としては、オキシシン（一般に8-キノリノール又は8-ヒドロキシキノリン）のキレートを含む金属キレートオキシノイド化合物、例えばトリス（8-キノリノール）アルミニウムを電子注入材料として用いることができる。

また、一般に、超薄膜に電界を印可するために、リークやショートによる画素欠陥が生じやすい。これを防止するために、一対の電極間に絶縁性の薄膜層を挿

入しても良い。

絶縁層に用いられる材料としては、例えば、酸化アルミニウム、弗化リチウム、酸化リチウム、弗化セシウム、酸化セシウム、酸化マグネシウム、弗化マグネシウム、酸化カルシウム、弗化カルシウム、窒化アルミニウム、酸化チタン、酸化珪素、酸化ゲルマニウム、窒化珪素、窒化ホウ素、酸化モリブデン、酸化ルテニウム、酸化バナジウム等が挙げられる。これらの混合物や積層物を用いてもよい。

次に、本発明の有機EL素子を作製する方法については、例えば上記の材料及び方法により陽極、発光層、必要に応じて正孔注入層、及び必要に応じて電子注入層を形成し、最後に陰極を形成すればよい。また、陰極から陽極へ、前記と逆の順序で有機EL素子を作製することもできる。

以下、透光性基板上に、陽極／正孔注入層／発光層／電子注入層／陰極が順次設けられた構成の有機EL素子の作製例について説明する。

まず、適当な透光性基板上に、陽極材料からなる薄膜を $1\mu\text{m}$ 以下、好ましくは $10\sim 200\text{nm}$ の範囲の膜厚になるように、蒸着法あるいはスパッタリング法により形成し、陽極とする。次に、この陽極上に正孔注入層を設ける。正孔注入層の形成は、前述したように真空蒸着法、スピンコート法、キャスト法、LB法等の方法により行うことができるが、均質な膜が得られやすく、かつピンホールが発生しにくい等の点から真空蒸着法により形成することが好ましい。真空蒸着法により正孔注入層を形成する場合、その蒸着条件は使用する化合物（正孔注入層の材料）、目的とする正孔注入層の結晶構造や再結合構造等により異なるが、一般に蒸着源温度 $50\sim 450^{\circ}\text{C}$ 、真空度 $10^{-7}\sim 10^{-3}\text{torr}$ 、蒸着速度 $0.01\sim 50\text{nm/秒}$ 、基板温度 $-50\sim 300^{\circ}\text{C}$ 、膜厚 $5\text{nm}\sim 5\mu\text{m}$ の範囲で適宜選択することが好ましい。

次に、この正孔注入層上に発光層を設ける。この発光層の形成も、本発明に係る発光材料を用いて真空蒸着法、スパッタリング、スピンコート法、キャスト法

等の方法により、発光材料を薄膜化することにより形成できるが、均質な膜が得られやすく、かつピンホールが発生しにくい等の点から真空蒸着法により形成することが好ましい。真空蒸着法により発光層を形成する場合、その蒸着条件は使用する化合物により異なるが、一般的に正孔注入層の形成と同様な条件範囲の中から選択することができる。膜厚は10～40 nmの範囲が好ましい。

次に、この発光層上に電子注入層を設ける。この場合にも正孔注入層、発光層と同様、均質な膜を得る必要から真空蒸着法により形成することが好ましい。蒸着条件は正孔注入層、発光層と同様の条件範囲から選択することができる。

そして、最後に陰極を積層して有機EL素子を得ることができる。陰極は金属から構成されるもので、蒸着法、スパッタリングを用いることができる。しかし、下地の有機物層を製膜時の損傷から守るためには真空蒸着法が好ましい。

以上の有機EL素子の作製は、一回の真空引きで、一貫して陽極から陰極まで作製することが好ましい。

この有機EL素子に直流電圧を印加する場合、陽極を＋、陰極を－の極性にして、3～40 Vの電圧を印加すると、発光が観測できる。また、逆の極性で電圧を印加しても電流は流れず、発光は全く生じない。さらに、交流電圧を印加した場合には、陽極が＋、陰極が－の極性になった時のみ均一な発光が観測される。この場合、印加する交流の波形は任意でよい。

次に、本発明を実施例によりさらに詳細に説明するが、本発明は、これらの例によってなんら限定されるものではない。

合成例1 (10-(2-ナフチル)アントラセン-9-ボロン酸の合成)

Ar雰囲気下、20リットルのフラスコに、2-ナフタレンボロン酸549g (東京化成社製)、9-ブロモアントラセン684g (東京化成社製)、テトラキス(トリフェニルホスフィン)パラジウム(0) 61.5g (東京化成社製)、トルエン 4.9リットル (広島和光社製) 及び炭酸ナトリウム845.9g (広島和光社製) を水 4.9リットル

ルに溶解したものを入れ、還流しながら24時間加熱撹拌を行った。反応後、室温まで冷却し、析出した結晶を濾取した。これをトルエンで再結晶し、751gの結晶を得た。

Ar雰囲気下、20リットルのフラスコに、この結晶750gと脱水処理したDMF(ジメチルホルムアミド) 10リットル(広島和光社製)を入れ、80℃に加熱し、原料を溶解後、50℃でN-ブロモコハク酸イミド482.4g(広島和光社製)を加え、2時間撹拌した。反応終了後、精製水20リットルの中に反応液を注入し、析出した結晶を濾取した。これをトルエンで再結晶し、689gの結晶を得た。

Ar雰囲気下、20リットルのフラスコに、この結晶588gと脱水処理したエーテル4.5リットル(広島和光社製)及び脱水処理したトルエン4.5リットル(広島和光社製)を加え、ドライアイスバスにて-64℃にした。これに1.6Mブチルリチウム/ヘキサン溶液1.2リットル(広島和光社製)を30分かけて滴下し、-64℃にて2時間反応させた。これにボロン酸トリイソプロピルエステル866g(東京化成社製)を20分間かけて滴下した。滴下後室温に戻し、12時間撹拌した。これを氷冷し、10℃以下にて2Nの塩酸を4リットル添加し、トルエン1リットルを加えた。これを分液し、硫酸ナトリウムで乾燥後、減圧濃縮し、ヘキサンを加え、析出した結晶を濾取した。これをTHF(テトラヒドロフラン)5リットルに溶解させ、濃塩酸500ミリリットル、テトラブチルアンモニウムブロマイド5gを添加し、12時間撹拌した。析出した結晶を濾取し、乾燥後、431gの結晶が得られた。

この化合物のFD-MS(フィールドディソープションマス分析)を測定したところ、 $C_{24}H_{17}BO_2=348$ に対し、 $m/z=348$ が得られたことから、この化合物を10-(2-ナフチル)アントラセン-9-ボロン酸と同定した(収率47%)。

合成例2 (2-(4-ブロモフェニル)ナフタレンの合成)

Ar雰囲気下、300ミリリットルのフラスコに、2-ナフタレンボロン酸7.1g(東京化成社製)、4-ヨードブロモベンゼン12.9g(東京化成社製)、テトラキス(トリフェニルホスフィン)パラジウム(0)0.6g(東京化成社製)、炭酸ナトリ

ウム 12.7g (広島和光社製) を水60ミリリットルに溶解したものを入れ、還流しながら24時間加熱攪拌を行った。反応後、室温まで冷却し、析出した結晶を濾取した。これをトルエンで再結晶し、9.0gの結晶を得た。

この化合物のFD-MS を測定したところ、 $C_{16}H_{11}Br=283$ に対し、 $m/z=284$ 、282 が得られたことから、この化合物を2-(4-プロモフェニル)ナフタレンと同一とした(収率77%)。

合成例3 (3-(4-プロモフェニル)フルオランテンの合成)

Ar雰囲気下、500ミリリットルのフラスコにフルオランテン 62gと脱水処理したDMF250ミリリットル(広島和光社製)を入れ、80℃に加熱し、原料を溶解後、50℃でN-プロモコハク酸イミド 60g(広島和光社製)を加え、2時間攪拌した。反応終了後、精製水 500ミリリットルの中に反応液を注入し、析出した結晶を濾取した。これをカラムクロマトグラフィーで精製し、10.5gの結晶を得た。

Ar雰囲気下、500ミリリットルのフラスコにこの結晶 10.0gと脱水処理したエーテル 120ミリリットル(広島和光社製)及び脱水処理したトルエン 120ミリリットル(広島和光社製)を加え、ドライアイスバスにて-64℃にした。1.6Mブチルリチウム/ヘキサン溶液25ミリリットル(広島和光社製)を30分かけて滴下し、-64℃にて2時間反応させた。これにボロン酸トリイソプロピルエステル8g(東京化成社製)を20分間かけて滴下した。滴下後室温に戻し、12時間攪拌した。これを氷冷し、10℃以下にて2Nの塩酸を 100ミリリットル添加し、トルエン25ミリリットルを加えた。これを分液し、硫酸ナトリウムで乾燥後、減圧濃縮し、ヘキサンを加え、析出した結晶を濾取した。これをTHF120ミリリットルに溶解させ、濃塩酸15ミリリットル、テトラブチルアンモニウムブロマイド 0.15gを添加し、12時間攪拌した。析出した結晶を濾取し、乾燥後、7.0gの3-フルオランテンボロン酸の結晶が得られた。

Ar雰囲気下、300ミリリットルのフラスコに、この結晶7.0g(東京化成社製)、4-ヨードプロモベンゼン9.0g(東京化成社製)、テトラキス(トリフェニルホ

スフィン) パラジウム (0) 0.6g (東京化成社製)、炭酸ナトリウム 12.7g (広島和光社製) を水60ミリリットルに溶解したものを、還流しながら24時間加熱攪拌を行った。反応後、室温まで冷却し、析出した結晶を濾取した。これをトルエンで再結晶し、6.4gの結晶を得た。

この化合物のFD-MS を測定したところ、 $C_{22}H_{15}Br=357$ に対し、 $m/z=358$ 、356 が得られたことから、この化合物を3-(4-プロモフェニル)フルオランテンと同定した (収率6%)。

合成例4 (10-(3-フルオランテニル)アントラセン-9-ボロン酸の合成)

Ar雰囲気下、300ミリリットルのフラスコに、3-フルオランテンボロン酸7.85g、9-プロモアントラセン6.84g (東京化成社製)、テトラキス(トリフェニルホスフィン)パラジウム(0) 0.6g (東京化成社製)、トルエン50ミリリットル (広島和光社製) 及び炭酸ナトリウム8.5g (広島和光社製) を水50ミリリットルに溶解したものを、還流しながら24時間加熱攪拌を行った。反応後、室温まで冷却し、析出した結晶を濾取した。これをトルエンで再結晶し、4.6gの結晶を得た。

Ar雰囲気下、300ミリリットルのフラスコにこの結晶4.5gと脱水処理したDMF100ミリリットル (広島和光社製) を入れ、80℃に加熱し、原料を溶解後、50℃でN-プロモコハク酸イミド2.3g (広島和光社製) を加え、2時間攪拌した。反応終了後、精製水 200ミリリットルの中に反応液を注入し、析出した結晶を濾取した。これをトルエンで再結晶し、4.5gの結晶を得た。

Ar雰囲気下、300ミリリットルのフラスコにこの結晶4.5gと脱水処理したエーテル50ミリリットル (広島和光社製) 及び脱水処理したトルエン50ミリリットル (広島和光社製) を加え、ドライアイスバスにて-64℃にした。1.6Mブチルリチウム/ヘキサン溶液7ミリリットル (広島和光社製) を30分かけて滴下し、-64℃にて2時間反応させた。これにボロン酸トリイソプロピルエステル5.6g (東京化成社製) を20分間かけて滴下した。滴下後室温に戻し、12時間攪拌した。これ

を氷冷し、10℃以下にて2Nの塩酸を40ミリリットル添加し、トルエン10ミリリットルを加えた。これを分液し、硫酸ナトリウムで乾燥後、減圧濃縮し、ヘキサンを加え、析出した結晶を濾取した。これをTHF 50ミリリットルに溶解させ、濃塩酸5ミリリットル、テトラブチルアンモニウムブロマイド0.1gを添加し、12時間攪拌した。析出した結晶を濾取し、乾燥後、3.6gの結晶が得られた。

この化合物のFD-MS を測定したところ、 $C_{30}H_{19}BO_2=422$ に対し、 $m/z=422$ が得られたことから、この化合物を10-(3-フルオランテニル) アントラセン-9-ボロン酸と同定した(収率32%)。

合成例5 (1-(4-プロモフェニル)ナフタレンの合成)

合成例2において、2-ナフタレンボロン酸の代わりに1-ナフタレンボロン酸を用いた以外は同様に実施し、無色の油状物29.9gを得た。

この化合物のFD-MS を測定したところ、 $C_{16}H_{11}Br=283$ に対し、 $m/z=284$, 282 が得られたことから、この化合物を1-(4-プロモフェニル)ナフタレンと同定した(収率88%)。

合成例6 (2-(3-プロモフェニル)ナフタレンの合成)

合成例2において、4-ヨードプロモベンゼンの代わりに3-ヨードプロモベンゼンを用いた以外は同様に実施し、無色の油状物20.1gを得た。

この化合物のFD-MS を測定したところ、 $C_{16}H_{11}Br=283$ に対し、 $m/z=284$, 282 が得られたことから、この化合物を2-(3-プロモフェニル)ナフタレンと同定した(収率75%)。

実施例1 (化合物(AN8)の合成)

Ar雰囲気下、300ミリリットルのフラスコに、合成例1で得られた10-(2-ナフチル)アントラセン-9-ボロン酸5.98g、合成例2で得られた2-(4-プロモフェニル)ナフタレン4.05g、テトラキス(トリフェニルホスフィン)パラジウム(0)0.33g(東京化成社製)、1,2-ジメトキシエタン60ミリリットル(広島和光社製)及び炭酸ナトリウム4.55g(広島和光社製)を水21ミリリットルに溶解し

たものを入れ、還流しながら24時間加熱攪拌を行った。反応後、室温まで冷却し、析出した結晶を濾取した。この化合物をカラムクロマトグラフィーにて精製し、3.4gの淡黄色固体を得た。

この化合物のFD-MS を測定したところ、 $C_{16}H_{14}=506$ に対し、 $m/z=506$ が得られたことから、この化合物をAN 8 と同定した（収率47%）。

実施例 2（化合物（AN 10）の合成）

Ar雰囲気下、300ミリリットルのフラスコに、合成例1で得られた10-(2-ナフチル)アントラセン-9-ボロン酸 5.98g、合成例3で得られた3-(4-プロモフェニル)フルオランテン5.13g、テトラキス(トリフェニルホスフィン)パラジウム(0) 0.33g（東京化成社製）、1,2-ジメトキシエタン60ミリリットル（広島和光社製）及び炭酸ナトリウム 4.55g（広島和光社製）を水21ミリリットルに溶解したものを入れ、還流しながら24時間加熱攪拌を行った。反応後、室温まで冷却し、析出した結晶を濾取した。この化合物をカラムクロマトグラフィーにて精製し、3.3gの淡黄色固体を得た。

この化合物のFD-MS を測定したところ、 $C_{16}H_{14}=580$ に対し、 $m/z=580$ が得られたことから、この化合物をAN 10 と同定した（収率40%）。

実施例 3（化合物（AN 28）の合成）

Ar雰囲気下、300ミリリットルのフラスコに、合成例4で得られた10-(3-フルオランテニル)アントラセン-9-ボロン酸 7.24g、合成例2で得られた2-(4-プロモフェニル)ナフタレン 4.05g、テトラキス(トリフェニルホスフィン)パラジウム(0) 0.33g（東京化成社製）、1,2-ジメトキシエタン60ミリリットル（広島和光社製）及び炭酸ナトリウム 4.55g（広島和光社製）を水21ミリリットルに溶解したものを入れ、還流しながら24時間加熱攪拌を行った。反応後、室温まで冷却し、析出した結晶を濾取した。この化合物をカラムクロマトグラフィーにて精製し、3.6gの淡黄色固体を得た。

この化合物のFD-MS は $C_{16}H_{14}=580$ に対し、 $m/z=580$ が得られたことから、

この化合物をAN 28と同定した（収率43%）。

実施例4（化合物（AN 30）の合成）

Ar雰囲気下、300ミリリットルのフラスコに、合成例4で得られた10-(3-フルオランテニル)アントラセン-9-ボロン酸 7.24g、合成例3で得られた3-(4-ブロモフェニル)フルオランテン 5.13g、テトラキス（トリフェニルホスフィン）パラジウム（0）0.33g（東京化成社製）、1,2-ジメトキシエタン60ミリリットル（広島和光社製）及び炭酸ナトリウム 4.55g（広島和光社製）を水21ミリリットルに溶解したものを入れ、還流しながら24時間加熱攪拌を行った。反応後、室温まで冷却し、析出した結晶を濾取した。この化合物をカラムクロマトグラフィーにて精製し、3.1gの淡黄色固体を得た。


この化合物のFD-MS は $C_{52}H_{30}=654$ に対し、 $m/z=654$ が得られたことから、この化合物をAN 30と同定した（収率33%）。

実施例5（有機EL素子の製造）


25mm×75mm×1.1mm厚のITO透明電極付きガラス基板（ジオマティック社製）をイソプロピルアルコール中で超音波洗浄を5分間行なった後、UVオゾン洗浄を30分間行なった。洗浄後の透明電極ライン付きガラス基板を真空蒸着装置の基板ホルダーに装着し、まず透明電極ラインが形成されている側の面上に前記透明電極を覆うようにして膜厚60nmの下記N, N'-ビス（N, N'-ジフェニル-4-アミノフェニル）-N, N'-ジフェニル-4, 4'-ジアミノ-1, 1'-ビフェニル膜（以下、TPD 232膜）を成膜した。このTPD 232膜は、正孔注入層として機能する。続いて、このTPD 232膜上に膜厚20nmの下記N, N, N', N'-テトラ（4-ビフェニル）-ジアミノビフェニレン膜（以下、TBDB膜）を成膜した。この膜は正孔輸送層として機能する。さらにTBDB膜上に、発光材料として膜厚40nmの化合物（AN 8）を蒸着し成膜した。同時に発光分子として、下記のスチリル基を有する下記アミン化合物D1をAN 8に対し、重量比でAN 8 : D1 = 40 : 2で蒸着した

。この膜は、発光層として機能する。この膜上に膜厚10nmのAlq膜を成膜した。これは、電子注入層として機能する。その後、還元性ドパントであるLi（Li源：サエスゲッター社製）とAlqを二元蒸着させ、電子注入層（陰極）としてAlq:Li膜（膜厚10nm）を形成した。このAlq:Li膜上に金属Alを蒸着させ金属陰極を形成し有機EL素子を製造した。


得られた有機EL素子について、発光効率と、初期輝度を1000nitで通常の使用環境下での半減寿命を測定した。それらの結果を表1に示す。




TPD232



TBDB



D 1




Alq

実施例6～8（有機EL素子の製造）

実施例5において、発光材料として、AN8の代わりに表1に記載の化合物を用いたこと以外は同様にして有機EL素子を製造し、発光効率と、初期輝度を1000nitで通常の使用環境下での半減寿命を測定した。それらの結果を表1に示す。

実施例 9 (有機 EL 素子の製造)

実施例 5 において、スチリル基を有するアミン化合物 D 1 の代わりに、下記芳香族アミン D 2 を用いたこと以外は同様にして有機 EL 素子を製造し、発光効率と、初期輝度を 1000nit で通常の使用環境下での半減寿命を測定した。それらの結果を表 1 に示す。



実施例 10 (化合物 (AN 5) の合成)

実施例 1 において、2-(4-プロモフェニル)ナフタレンの代わりに、3,5-ジフェニルプロモベンゼンを用いた以外は同様に実施し、5.6gの淡黄色固体を得た。

この化合物のFD-MS を測定したところ、 $C_{12}H_{10}Br$ = 532 に対し $m/z = 532$ が得られたことから、この化合物を AN 5 と同定した (収率 45%)。

実施例 11 (化合物 (AN 7) の合成)

実施例 1 において、2-(4-プロモフェニル)ナフタレンの代わりに、1-(4-プロモフェニル)ナフタレンを用いた以外は同様に実施し、7.8gの淡黄色固体を得た。

この化合物のFD-MS を測定したところ、 $C_{10}H_{10}Br$ = 506 に対し $m/z = 506$ が得られたことから、この化合物を AN 7 と同定した (収率 54%)。

実施例 12 (化合物 (AN 49) の合成)

実施例 1 において、2-(4- ブロモフェニル) ナフタレンの代わりに、2-(3- ブロモフェニル) ナフタレンを用いた以外は同様に実施し、6.9gの淡黄色固体を得た。


この化合物のFD-MS を測定したところ、 $C_{16}H_{10}Br=506$ に対し $m/z=506$ が得られたことから、この化合物をAN 4 9 と同定した (収率52%)。

実施例 1 3 ~ 1 5 (有機EL素子の製造)

実施例 5 において、発光材料として、AN 8 の代わりに表 1 に記載の化合物を用いたこと以外は同様にして有機EL素子を製造し、発光効率と、初期輝度を1000nit で通常の使用環境下での半減寿命を測定した。それらの結果を表 1 に示す。


比較例 1 (有機EL素子の製造)

実施例 5 において、発光材料として、AN 8 の代わりにan 1を用いたこと以外は同様にして有機EL素子を製造し、発光効率と、初期輝度を1000nit で通常の使用環境下での半減寿命を測定した。それらの結果を表 1 に示す。



比較例 2 (有機EL素子の製造)

実施例 5 において、発光材料として、AN 8 の代わりにan 2を用いたこと以外は同様にして有機EL素子を製造し、発光効率と、初期輝度を1000nit で通常の使用環境下での半減寿命を測定した。それらの結果を表 1 に示す。



a n 2

表 1

	発光層の化合物	発光効率 (cd/A)	半減寿命 (時間)	発光色
実施例5	AN8/D1	11.2	4200	青色
実施例6	AN10/D1	11.0	4000	青色
実施例7	AN28/D1	10.9	3700	青色
実施例8	AN30/D1	10.8	3700	青色
実施例9	AN8/D2	10.6	3200	青色
実施例13	AN5/D1	11.0	2200	青色
実施例14	AN7/D1	11.3	4500	青色
実施例15	AN49/D1	11.3	4500	青色
比較例1	an1/D1	9.0	2200	青色
比較例2	an2/D1	8.8	1100	青色


表1に示したように、実施例5～9及び13～15の有機EL素子は、発光効率が高く、極めて長寿命であった。これに対し、比較例1及び2の有機EL素子は、発光効率が低い上、寿命も短かった。

産業上の利用可能性

以上、詳細に説明したように、本発明の有機EL素子及び本発明のアントラセン誘導体を用いた有機EL素子は、発光効率が高く、長寿命である。このため、長期間の継続使用が想定される有機EL素子として有用である。

請求の範囲

1. 陰極と陽極間に少なくとも発光層を含む一層又は複数層からなる有機薄膜層が挟持されている有機エレクトロルミネッセンス素子において、該有機薄膜層の少なくとも1層が、下記一般式(1)で表されるアントラセン誘導体を単独もしくは混合物の成分として含有する有機エレクトロルミネッセンス素子。




(式中、Arは置換もしくは無置換の核炭素数10～50の縮合芳香族基である。

Ar'は置換もしくは無置換の核炭素数6～50の芳香族基である。

Xは、置換もしくは無置換の核炭素数6～50の芳香族基、置換もしくは無置換の核原子数5～50の芳香族複素環基、置換もしくは無置換の炭素数1～50のアルキル基、置換もしくは無置換の炭素数1～50のアルコキシ基、置換もしくは無置換の炭素数6～50のアラルキル基、置換もしくは無置換の核原子数5～50のアリールオキシ基、置換もしくは無置換の核原子数5～50のアリールチオ基、置換もしくは無置換の炭素数1～50のアルコシカルボニル基、カルボキシル基、ハロゲン原子、シアノ基、ニトロ基、ヒドロキシル基である。


a、b及びcは、それぞれ0～4の整数である。

nは1～3の整数である。また、nが2以上の場合は、[]内の



は、同じでも異なってもよい。)

2. 前記一般式(1)におけるArが、下記の一般式




(Ar₁は、置換もしくは無置換の核炭素数6～50の芳香族基である。)から選ばれる基である請求項1に記載の有機エレクトロルミネッセンス素子。

3. 前記発光層が、一般式(1)で表されるアントラセン誘導体を主成分として含有する請求項1に記載の有機エレクトロルミネッセンス素子。

4. 前記発光層が、さらにアリールアミン化合物を含有する請求項1に記載の有機エレクトロルミネッセンス素子。

5. 前記発光層が、さらにスチリルアミン化合物を含有する請求項1に記載の有機エレクトロルミネッセンス素子。

6. 下記一般式(2)で表されるアントラセン誘導体。




(式中、Arは置換もしくは無置換の核炭素数10～50の縮合芳香族基である。

Ar'は置換もしくは無置換の核炭素数6～50の芳香族基である。

Xは、置換もしくは無置換の核炭素数6～50の芳香族基、置換もしくは無置換の核原子数5～50の芳香族複素環基、置換もしくは無置換の炭素数1～50のアルキル基、置換もしくは無置換の炭素数1～50のアルコキシ基、置換もしくは無置換の炭素数6～50のアラルキル基、置換もしくは無置換の核原子数5～50のアリールオキシ基、置換もしくは無置換の核原子数5～50のアリールチオ基、置換もしくは無置換の炭素数1～50のアルコキシカルボニル基、カルボキシル基、ハロゲン原子、シアノ基、ニトロ基、ヒドロキシル基である。

a及びbは、それぞれ0～4の整数である。

nは1～3の整数である。また、nが2以上の場合は、[]内の



は、同じでも異なってもよい。)

7. 有機エレクトロルミネッセンス素子用材料である請求項6に記載のアントラセン誘導体。

8. 陰極と陽極間に少なくとも発光層を含む一層又は複数層からなる有機薄膜層が挟持されている有機エレクトロルミネッセンス素子において、該有機薄膜層の少なくとも1層が、請求項6に記載の一般式(2)で表されるアントラセン誘導体を単独もしくは混合物の成分として含有する有機エレクトロルミネッセンス素子。

(12) INTERNATIONAL PATENT OFFICE
WORLD ORGANIZATION FOR INTELLECTUAL PROPERTY

(19) International patent published on
the basis of the Patent Cooperation Treaty

(10) INTERNATIONAL PUBLICATION NO. WO 2004/018587

(51) International Patent Cl. ^x :	C09K 11/06 A
(21) International Application No.:	PCT/JP2003/010402
(22) International Application Date:	August 18, 2003
(43) International Publication Date:	March 4, 2004
(30) Priority	
Date:	August 23, 2002
Country:	Japan
No.:	2002-243545
(72) Inventor(s) and	
(75) Inventor(s)/Applicant(s) (only for US):	Hidetsugu Ikeda 1280 Kamiizumi Sodegaura, Chiba 299-0205 Motohisa Ido 1280 Kamiizumi Sodegaura, Chiba 299-0205 Masakazu Funabashi 1280 Kamiizumi Sodegaura, Chiba 299-0205
(71) Applicant(s) (for all designated States except US):	Idemitsu Kosan Co., Ltd. 3-1-1 Marunouchi

Chiyoda-ku, Tokyo 100-8321

(74) Agent:

Tamotsu Otani et al.
Bridgestone Toranomon Bldg. 6F
3-25-2 Toranomon
Minato-ku, Tokyo 105-0001

(81) Designated States (national): CN, IN, JP, KR, US

(84) Designated States (regional): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR)

Published with International Search Report

(54) Title: ORGANIC ELECTROLUMINESCENCE DEVICE AND ANTHRACENE
DERIVATIVE

(57) Abstract: An organic electroluminescence device comprising a negative electrode and a positive electrode and, interposed therebetween, one or two or more organic thin-film layers including at least a luminescent layer, wherein at least one of the organic thin-film layers contains an anthracene derivative of specified structure added alone or as a component of mixture; and an anthracene derivative of asymmetric specified structure. There are provided an organic electroluminescence device of high luminescence efficiency and long life and an anthracene derivative for realizing the same.

Technological field

The present invention concerns organic electroluminescent devices and anthracene derivatives, and more specifically concerns organic electroluminescent devices having a high luminescence efficiency and long life, as well as anthracene derivatives making such devices possible.

Background technology

The organic electroluminescent devices (hereafter, electroluminescence is abbreviated EL) are self-illuminating devices utilizing the principle of emission of light from phosphors by recombination energy between positive holes injected by a positive electrode and electrons injected by a negative electrode upon the application of an electric field. Since the report of C.W. Tang et al.: Low-voltage organic EL devices by laminated devices (C.W. Tang, S.A. Vanslyke: Applied Physics Letters, vol 51, 913, 1987) of the Eastman Kodak Co., many studies have been carried out concerning organic EL devices using organic substances as constituting materials. Tang et al. used tris(8-hydroxyquinolyl)aluminum in the luminescence layer and a triphenyldiamine derivative in the positive-hole transport layer. Advantages of a laminated structure include an enhanced injection efficiency of the positive holes into the luminescence layer, enhanced efficiency of the formation of excitons formed by recombination, blocking the electrons injected from the negative electrode, capture of excitons formed in the luminescence layer, etc. As shown in this example, a two-layer type of positive hole transport (injection) layer and electron transport luminescence layer, three-layer type of positive hole transport (injection) layer, luminescence layer, and electron transport (injection) layer, etc., are well known for the device structure of organic EL devices. In such laminate-type-structure devices, the device structure and formation processes have been studied for enhancing the recombination efficiency of the injected positive holes and electrons.

Also, chelate complexes such as tris(8-quinolinolato)aluminum complex, etc., coumarin derivatives, tetraphenylbutadiene derivatives, bisstyrylarylene derivatives, oxadiazole derivatives, etc., have been known as luminescent materials. It has been reported that visible light ranging from blue to red can be obtained from them, and the realization of color display devices is expected (e.g., Japanese Kokai Patent No. HEI 8[1996]-239655, HEI 7[1995]-138561, HEI 3[1991]-200289, etc.).

Also, devices using phenylanthracene derivatives as luminescent materials have been disclosed in Japanese Kokai Patent No. HEI 8[1996]-012600. Such anthracene derivatives are used as blue [-light] emitting materials, while a longer device service life is desirable. Furthermore, device materials having fluoranthene groups at the 9 and 10 positions of anthracene were disclosed in Japanese Kokai Patent No. 2001-257074. These anthracene derivatives are also blue emitting materials, yet an improved device service life is necessary. Use of various


anthracene derivatives for positive-hole transporting materials was disclosed in Japanese Kokai Patent No. 2000-182776. However, their syntheses have not been carried out in practice, and their evaluation as luminescent materials is incomplete.

Disclosure of the invention


It is an objective of the present invention to overcome such problems and to provide anthracene derivatives enabling the realization of long-life organic EL devices with a high luminescence efficiency.

As a result of an intense study for achieving such objectives, we have discovered that long-life organic EL devices with a high luminescence efficiency can be obtained by using anthracene compounds having a certain asymmetric structure shown by general formula (1) or (2) as luminescence materials of organic EL devices. Thus, the present invention is attained.


Namely, the present invention provides organic electroluminescence devices having at least one luminescence-layer-containing organic thin film layer sandwiched between a positive electrode and negative electrode, wherein at least one layer of the organic thin film layer contains the anthracene derivative represented by general formula (1) or (2) shown below, alone or as a component in a mixture:




(In the formula, Ar is an (un)substituted condensed aromatic group of 10-50 nuclear carbon atoms; Ar' is an (un)substituted aromatic group of 6-50 nuclear carbon atoms; X is an (un)substituted aromatic group of 6-50 nuclear carbon atoms, (un)substituted aromatic heterocyclic group of 5-50 nuclear carbon atoms, (un)substituted alkyl group of 1-50 carbon atoms, (un)substituted alkoxy group of 1-50 carbon atoms, (un)substituted aralkyl group of 6-50 carbon atoms, (un)substituted aryloxy group of 5-50 nuclear carbon atoms, (un)substituted arylthio group of 5-50 nuclear carbon atoms, (un)substituted alkoxycarbonyl group of 1-50 carbon atoms, carboxy group, halogen atom, cyano group, nitro group, or hydroxy group; a, b, and c are whole numbers of 0-4; and n is a whole number of 1-3; when n is 2 or more, the formula inside the parenthesis shown below may be the same or different:



Furthermore, the present invention provides anthracene derivatives represented by general formula (2) shown below:



(In the formula, Ar is an (un)substituted condensed aromatic group of 10-50 nuclear carbon atoms; Ar' is an (un)substituted aromatic group of 6-50 nuclear carbon atoms; X is an (un)substituted aromatic group of 6-50 nuclear carbon atoms, (un)substituted aromatic heterocyclic group of 5-50 nuclear carbon atoms, (un)substituted alkyl group of 1-50 carbon atoms, (un)substituted alkoxy group of 1-50 carbon atoms, (un)substituted aralkyl group of 6-50 carbon atoms, (un)substituted aryloxy group of 5-50 nuclear carbon atoms, (un)substituted arylthio group of 5-50 nuclear carbon atoms, (un)substituted alkoxycarbonyl group of 1-50 carbon atoms, carboxy group, halogen atom, cyano group, nitro group, or hydroxy group; a, b, and c are whole numbers of 0-4; and n is a whole number of 1-3; when n is 2 or more, the formula inside the parenthesis shown below may be the same or different:




Best embodiments for practicing the invention

The present invention provides organic electroluminescence devices having at least one luminescence-layer-containing organic thin film layer sandwiched between the positive electrode and negative electrode, wherein at least one layer of the organic thin film layer contains the anthracene derivative represented by general formula (1) shown above, alone or as a component in a mixture.

In general formula (1), Ar is an (un)substituted condensed aromatic group of 10-50 nuclear carbon atoms.

The condensed aromatic group may be, e.g., a 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, etc.

The preferred condensed aromatic group of Ar can be selected from the general formulas given below:



(Ar₁ is an (un)substituted aromatic group of 6-50 nuclear carbon atoms.)

Ar₁ may be, e.g., a phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4''-t-butyl-p-terphenyl-4-yl group, etc.

In general formula (1), Ar' is an (un)substituted aromatic group of 6-50 nuclear carbon atoms. Such an aromatic group may be a phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-

3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4''-t-butyl-p-terphenyl-4-yl group, etc.

Of these, especially preferred are (un)substituted aromatic groups of 10 or more nuclear carbon atoms, such as a 1-naphthyl group, 2-naphthyl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, etc.

In general formula (1), X is an (un)substituted aromatic group of 6-50 nuclear carbon atoms, (un)substituted aromatic heterocyclic group of 5-50 nuclear carbon atoms, (un)substituted alkyl group of 1-50 carbon atoms, (un)substituted alkoxy group of 1-50 carbon atoms, (un)substituted aralkyl group of 6-50 carbon atoms, (un)substituted aryloxy group of 5-50 nuclear carbon atoms, (un)substituted arylthio group of 5-50 nuclear carbon atoms, (un)substituted alkoxycarbonyl group of 1-50 carbon atoms, carboxy group, halogen atom, cyano group, nitro group, or hydroxy group.

Examples of the (un)substituted aromatic groups in X are the phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4''-t-butyl-p-terphenyl-4-yl group, etc.

Examples of the (un)substituted aromatic heterocyclic groups in X are the 1-pyrrolyl group, 2-pyrrolyl group, 3-pyrrolyl group, pyrazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 1-indolyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 2-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl

group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxaliny group, 5-quinoxaliny group, 6-quinoxaliny group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 9-carbazolyl group, 1-phenanthridiny group, 2-phenanthridiny group, 3-phenanthridiny group, 4-phenanthridiny group, 6-phenanthridiny group, 7-phenanthridiny group, 8-phenanthridiny group, 9-phenanthridiny group, 10-phenanthridiny group, 1-acridiny group, 2-acridiny group, 3-acridiny group, 4-acridiny group, 9-acridiny group, 1,7-phenanthrolin-2-yl group, 1,7-phenanthrolin-3-yl group, 1,7-phenanthrolin-4-yl group, 1,7-phenanthrolin-5-yl group, 1,7-phenanthrolin-6-yl group, 1,7-phenanthrolin-8-yl group, 1,7-phenanthrolin-9-yl group, 1,7-phenanthrolin-10-yl group, 1,8-phenanthrolin-2-yl group, 1,8-phenanthrolin-3-yl group, 1,8-phenanthrolin-4-yl group, 1,8-phenanthrolin-5-yl group, 1,8-phenanthrolin-6-yl group, 1,8-phenanthrolin-7-yl group, 1,8-phenanthrolin-9-yl group, 1,8-phenanthrolin-10-yl group, 1,9-phenanthrolin-2-yl group, 1,9-phenanthrolin-3-yl group, 1,9-phenanthrolin-4-yl group, 1,9-phenanthrolin-5-yl group, 1,9-phenanthrolin-6-yl group, 1,9-phenanthrolin-7-yl group, 1,9-phenanthrolin-8-yl group, 1,9-phenanthrolin-10-yl group, 1,10-phenanthrolin-2-yl group, 1,10-phenanthrolin-3-yl group, 1,10-phenanthrolin-4-yl group, 1,10-phenanthrolin-5-yl group, 2,9-phenanthrolin-1-yl group, 2,9-phenanthrolin-3-yl group, 2,9-phenanthrolin-4-yl group, 2,9-phenanthrolin-5-yl group, 2,9-phenanthrolin-6-yl group, 2,9-phenanthrolin-7-yl group, 2,9-phenanthrolin-8-yl group, 2,9-phenanthrolin-10-yl group, 2,8-phenanthrolin-1-yl group, 2,8-phenanthrolin-3-yl group, 2,8-phenanthrolin-4-yl group, 2,8-phenanthrolin-5-yl group, 2,8-phenanthrolin-6-yl group, 2,8-phenanthrolin-7-yl group, 2,8-phenanthrolin-9-yl group, 2,8-phenanthrolin-10-yl group, 2,7-phenanthrolin-1-yl group, 2,7-phenanthrolin-3-yl group, 2,7-phenanthrolin-4-yl group, 2,7-phenanthrolin-5-yl group, 2,7-phenanthrolin-6-yl group, 2,7-phenanthrolin-8-yl group, 2,7-phenanthrolin-9-yl group, 2,7-phenanthrolin-10-yl group, 1-phenazinyl group, 2-phenazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 10-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 10-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrol-1-yl group, 2-methylpyrrol-3-yl group, 2-methylpyrrol-4-yl group, 2-methylpyrrol-5-yl group, 3-methylpyrrol-1-yl group, 3-methylpyrrol-2-yl group, 3-methylpyrrol-4-yl group, 3-methylpyrrole-5-yl group, 2-t-butylpyrrol-4-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, 4-t-butyl-3-indolyl group, etc.

Examples of the (un)substituted alkyl group in X are the methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-

pentyl group, n-hexyl group n-heptyl group, n-octyl group, hydroxymethyl group, 1-hydroxyethyl group, 2-hydroxyethyl group, 2-hydroxyisobutyl group, 1,2-dihydroxyethyl group, 1,3-dihydroxyisopropyl group, 2,3-dihydroxy-t-butyl group, 1,2,3-trihydroxypropyl group, chloromethyl group, 1-chloroethyl group, 2-chloroethyl group, 2-chloroisobutyl group, 1,2-dichloroethyl group, 1,3-dichloroisopropyl group, 2,3-dichloro-t-butyl group, 1,2,3-trichloropropyl group, bromomethyl group, 1-bromoethyl group, 2-bromoethyl group, 2-bromoisobutyl group, 1,2-dibromoethyl group, 1,3-dibromoisopropyl group, 2,3-dibromo-t-butyl group, 1,2,3-tribromopropyl group, iodomethyl group, 1-iodoethyl group, 2-iodoethyl group, 2-iodoisobutyl group, 1,2-diiodoethyl group, 1,3-diiodoisopropyl group, 2,3-diiodo-t-butyl group, 1,2,3-triiodopropyl group, aminomethyl group, 1-aminoethyl group, 2-aminoethyl group, 2-aminoisobutyl group, 1,2-diaminoethyl group, 1,3-diaminoisopropyl group, 2,3-diamino-t-butyl group, 1,2,3-triaminopropyl group, cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyanoisobutyl group, 1,2-dicyanoethyl group, 1,3-dicyanoisopropyl group, 2,3-dicyano-t-butyl group, 1,2,3-tricyanopropyl group, nitromethyl group, 1-nitroethyl group, 2-nitroethyl group, 2-nitroisobutyl group, 1,2-dinitroethyl group, 1,3-dinitroisopropyl group, 2,3-dinitro-t-butyl group, 1,2,3-trinitropropyl group, cyclopropyl group, cyclobutyl group, cyclopentyl group, cyclohexyl group, 4-methylcyclohexyl group, 1-adamantyl group, 2-adamantyl group, 1-norbornyl group, 2-norbornyl group, etc.

The (un)substituted alkoxy group is a group represented by $-OY$, and examples of Y are the methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group n-heptyl group, n-octyl group, hydroxymethyl group, 1-hydroxyethyl group, 2-hydroxyethyl group, 2-hydroxyisobutyl group, 1,2-dihydroxyethyl group, 1,3-dihydroxyisopropyl group, 2,3-dihydroxy-t-butyl group, 1,2,3-trihydroxypropyl group, chloromethyl group, 1-chloroethyl group, 2-chloroethyl group, 2-chloroisobutyl group, 1,2-dichloroethyl group, 1,3-dichloroisopropyl group, 2,3-dichloro-t-butyl group, 1,2,3-trichloropropyl group, bromomethyl group, 1-bromoethyl group, 2-bromoethyl group, 2-bromoisobutyl group, 1,2-dibromoethyl group, 1,3-dibromoisopropyl group, 2,3-dibromo-t-butyl group, 1,2,3-tribromopropyl group, iodomethyl group, 1-iodoethyl group, 2-iodoethyl group, 2-iodoisobutyl group, 1,2-diiodoethyl group, 1,3-diiodoisopropyl group, 2,3-diiodo-t-butyl group, 1,2,3-triiodopropyl group, aminomethyl group, 1-aminoethyl group, 2-aminoethyl group, 2-aminoisobutyl group, 1,2-diaminoethyl group, 1,3-diaminoisopropyl group, 2,3-diamino-t-butyl group, 1,2,3-triaminopropyl group, cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyanoisobutyl group, 1,2-dicyanoethyl group, 1,3-dicyanoisopropyl group, 2,3-dicyano-t-butyl group, 1,2,3-tricyanopropyl group, nitromethyl group, 1-nitroethyl group, 2-nitroethyl group, 2-nitroisobutyl group, 1,2-dinitroethyl group, 1,3-dinitroisopropyl group, 2,3-dinitro-t-butyl group, 1,2,3-trinitropropyl group, etc.

Examples of the (un)substituted aralkyl group are the benzyl group, 1-phenylethyl group, 2-phenylethyl group, 1-phenylisopropyl group, 2-phenylisopropyl group, phenyl-t-butyl group, α -naphthylmethyl group, 1- α -naphthylethyl group, 2- α -naphthylethyl group, 1- α -naphthylisopropyl group, 2- α -naphthylisopropyl group, β -naphthylmethyl group, 1- β -naphthylethyl group, 2- β -naphthylethyl group, 1- β -naphthylisopropyl group, 2- β -naphthylisopropyl group, 1-pyrrolylmethyl group, 2-(1-pyrrolyl)ethyl group, p-methylbenzyl group, m-methylbenzyl group, o-methylbenzyl group, p-bromobenzyl group, m-bromobenzyl group, o-bromobenzyl group, p-iodobenzyl group, m-iodobenzyl group, o-iodobenzyl group, p-hydroxybenzyl group, m-hydroxybenzyl group, o-hydroxybenzyl group, p-aminobenzyl group, m-aminobenzyl group, o-aminobenzyl group, p-nitrobenzyl group, m-nitrobenzyl group, o-nitrobenzyl group, p-cyanobenzyl group, m-cyanobenzyl group, o-cyanobenzyl group, 1-hydroxy-2-phenylisopropyl group, 1-chloro-2-phenylisopropyl group, etc.

The (un)substituted aryloxy group is represented by $-OY'$, and examples of Y' are the phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4''-t-butyl-p-terphenyl-4-yl group, 1-pyrrolyl group, 2-pyrrolyl group, 3-pyrrolyl group, pyrazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 1-indolyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, quinolyl group, 2-quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxalyl group, 5-quinoxalyl group, 6-quinoxalyl group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 1-phenanthridinyl group, 2-phenanthridinyl group, 3-phenanthridinyl group, 4-phenanthridinyl group, 6-phenanthridinyl group, 7-phenanthridinyl group, 8-phenanthridinyl group, 9-phenanthridinyl group, 10-

phenanthridinyl group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 6-acridinyl group, 1,7-phenanthrolin-2-yl group, 1,7-phenanthrolin-3-yl group, 1,7-phenanthrolin-4-yl group, 1,7-phenanthrolin-5-yl group, 1,7-phenanthrolin-6-yl group, 1,7-phenanthrolin-8-yl group, 1,7-phenanthrolin-9-yl group, 1,7-phenanthrolin-10-yl group, 1,8-phenanthrolin-2-yl group, 1,8-phenanthrolin-3-yl group, 1,8-phenanthrolin-4-yl group, 1,8-phenanthrolin-5-yl group, 1,8-phenanthrolin-6-yl group, 1,8-phenanthrolin-7-yl group, 1,8-phenanthrolin-9-yl group, 1,8-phenanthrolin-10-yl group, 1,9-phenanthrolin-2-yl group, 1,9-phenanthrolin-3-yl group, 1,9-phenanthrolin-4-yl group, 1,9-phenanthrolin-5-yl group, 1,9-phenanthrolin-6-yl group, 1,9-phenanthrolin-7-yl group, 1,9-phenanthrolin-8-yl group, 1,9-phenanthrolin-10-yl group, 1,10-phenanthrolin-2-yl group, 1,10-phenanthrolin-3-yl group, 1,10-phenanthrolin-4-yl group, 1,10-phenanthrolin-5-yl group, 2,9-phenanthrolin-1-yl group, 2,9-phenanthrolin-3-yl group, 2,9-phenanthrolin-4-yl group, 2,9-phenanthrolin-5-yl group, 2,9-phenanthrolin-6-yl group, 2,9-phenanthrolin-7-yl group, 2,9-phenanthrolin-8-yl group, 2,9-phenanthrolin-10-yl group, 2,8-phenanthrolin-1-yl group, 2,8-phenanthrolin-3-yl group, 2,8-phenanthrolin-4-yl group, 2,8-phenanthrolin-5-yl group, 2,8-phenanthrolin-6-yl group, 2,8-phenanthrolin-7-yl group, 2,8-phenanthrolin-9-yl group, 2,8-phenanthrolin-10-yl group, 2,7-phenanthrolin-1-yl group, 2,7-phenanthrolin-3-yl group, 2,7-phenanthrolin-4-yl group, 2,7-phenanthrolin-5-yl group, 2,7-phenanthrolin-6-yl group, 2,7-phenanthrolin-8-yl group, 2,7-phenanthrolin-9-yl group, 2,7-phenanthrolin-10-yl group, 1-phenazinyl group, 2-phenazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 10-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 10-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrol-1-yl group, 2-methylpyrrol-3-yl group, 2-methylpyrrol-4-yl group, 2-methylpyrrol-5-yl group, 3-methylpyrrol-1-yl group, 3-methylpyrrol-2-yl group, 3-methylpyrrol-4-yl group, 3-methylpyrrol-5-yl group, 2-t-butylpyrrol-4-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, 4-t-butyl-3-indolyl group, etc.

The (un)substituted arylthio group is represented by $-SY''$, and examples of Y'' are the phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenylyl group, 3-biphenylyl group, 4-biphenylyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-

terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4''-t-butyl-p-terphenyl-4-yl group, 2-pyrrolyl group, 3-pyrrolyl group, pyrazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, quinolyl group, 2-quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxalyl group, 5-quinoxalyl group, 6-quinoxalyl group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 1-phenanthridinyl group, 2-phenanthridinyl group, 3-phenanthridinyl group, 4-phenanthridinyl group, 6-phenanthridinyl group, 7-phenanthridinyl group, 8-phenanthridinyl group, 9-phenanthridinyl group, 10-phenanthridinyl group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenanthroline-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-3-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-3-yl group, 2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-3-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-phenanthroline-5-yl group, 2,7-phenanthroline-6-yl group, 2,7-phenanthroline-8-yl group, 2,7-phenanthroline-9-yl group, 2,7-phenanthroline-10-yl group, 1-

phenazinyl group, 2-phenazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrol-1-yl group, 2-methylpyrrol-3-yl group, 2-methylpyrrol-4-yl group, 2-methylpyrrol-5-yl group, 3-methylpyrrol-1-yl group, 3-methylpyrrol-2-yl group, 3-methylpyrrol-4-yl group, 3-methylpyrrol-5-yl group, 2-t-butylpyrrol-4-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, 4-t-butyl-3-indolyl group, etc.

The (un)substituted alkoxycarbonyl group is represented by -COOZ , and examples of Z are the methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, hydroxymethyl group, 1-hydroxyethyl group, 2-hydroxyethyl group, 2-hydroxyisobutyl group, 1,2-dihydroxyethyl group, 1,3-dihydroxyisopropyl group, 2,3-dihydroxy-t-butyl group, 1,2,3-trihydroxypropyl group, chloromethyl group, 1-chloroethyl group, 2-chloroethyl group, 2-chloroisobutyl group, 1,2-dichloroethyl group, 1,3-dichloroisopropyl group, 2,3-dichloro-t-butyl group, 1,2,3-trichloropropyl group, bromomethyl group, 1-bromoethyl group, 2-bromoethyl group, 2-bromoisobutyl group, 1,2-dibromoethyl group, 1,3-dibromoisopropyl group, 2,3-dibromo-t-butyl group, 1,2,3-tribromopropyl group, iodomethyl group, 1-iodoethyl group, 2-iodoethyl group, 2-iodoisobutyl group, 1,2-diiodoethyl group, 1,3-diiodoisopropyl group, 2,3-diiodo-t-butyl group, 1,2,3-triiodopropyl group, aminomethyl group, 1-aminoethyl group, 2-aminoethyl group, 2-aminoisobutyl group, 1,2-diaminoethyl group, 1,3-diaminoisopropyl group, 2,3-diamino-t-butyl group, 1,2,3-triaminopropyl group, cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyanoisobutyl group, 1,2-dicyanoethyl group, 1,3-dicyanoisopropyl group, 2,3-dicyano-t-butyl group, 1,2,3-tricyanopropyl group, nitromethyl group, 1-nitroethyl group, 2-nitroethyl group, 2-nitroisobutyl group, 1,2-dinitroethyl group, 1,3-dinitroisopropyl group, 2,3-dinitro-t-butyl group, 1,2,3-trinitropropyl group, etc.

Examples of the ring-forming divalent groups are the tetramethylene group, pentamethylene group, hexamethylene group, diphenylmethane-2,2'-di-yl group, diphenylethane-3,3'-di-yl group, diphenylpropane-4,4'-di-yl group, etc.

The halogen atom may be fluorine, chlorine, bromine, or iodine.


In general formula (1), a, b, and c independently represent whole numbers of 0-4, preferably 0-1.


The n is a whole number of 1-3. When n is 2 or more, the groups in [] may be the same or different.


Substituents on the groups represented by the above Ar, Ar', and X may be a halogen atom, hydroxy group, nitro group, cyano group, alkyl group, aryl group, cycloalkyl group, alkoxy group, aromatic heterocyclic group, aralkyl group, aryloxy group, arylthio group, alkoxycarbonyl group, or carboxy group.


Specific examples of the anthracene derivative represented by general formula (1) of the present invention are, but not limited to, those shown below. Me is a methyl group and Bu is a butyl group.


In the anthracene derivatives represented by general formula (1), both Ar and Ar' representing a naphthyl group and $a = b = c = 0$ are most preferred.














AN51




AN52




AN53




AN54




AN55




AN56




AN57




AN58



AN59



AN60



The anthracene derivatives represented by the above general formula (2) of the present invention, included in general formula (1), are novel compounds.

- In general formula (2), Ar is an (un)substituted condensed aromatic group of 10-50 nuclear carbon atoms.
- In general formula (2), Ar' is an (un)substituted aromatic group of 6-50 nuclear carbon atoms.
- In general formula (2), X is an (un)substituted aromatic group of 6-50 nuclear carbon atoms, (un)substituted aromatic heterocyclic group of 5-50 nuclear carbon atoms, (un)substituted alkyl group of 1-50 carbon atoms, (un)substituted alkoxy group of 1-50 carbon atoms, (un)substituted aralkyl group of 6-50 carbon atoms, (un)substituted aryloxy group of 5-50 nuclear carbon atoms, (un)substituted arylthio group of 5-50 nuclear carbon atoms, (un)substituted alkoxycarbonyl group of 1-50 carbon atoms, carboxy group, halogen atom, cyano group, nitro group, or hydroxy group.
- The specific examples of groups represented by Ar, Ar', and X are similar to those given for general formula (1).

Substituents on the groups represented by the above Ar, Ar', and X may be a halogen atom, hydroxy group, nitro group, cyano group, alkyl group, aryl group, cycloalkyl group, alkoxy group, aromatic heterocyclic group, aralkyl group, aryloxy group, arylthio group, alkoxycarbonyl group, or carboxy group.


In general formula (2), a and b independently represent whole numbers of 0-4, preferably 0-1.

The n is a whole number of 1-3. When n is 2 or more, the groups in [] may be the same or different.

Specific examples of the anthracene derivatives represented by general formula (2) of the present invention may be, but not limited to, (AN1)-(AN4), AN7)-(AN14), (AN17)-(AN24), (AN27)-(AN36), (AN39)-(AN43), and (AN46)-(AN48) given as specific examples of general formula (1).

The anthracene derivatives represented by general formula (2) of the present invention are preferred for organic EL device materials.

The anthracene derivatives of general formula (1) or (2), used in the organic EL devices of the present invention, can be synthesized by an appropriate combination of Suzuki coupling reaction, halogenation, and boration reaction of a commercially available arylboronic acid or arylboronic acid synthesized by a known method and using halogenated anthracene derivatives as starting materials. The synthesis scheme is shown below.



There have been many reports of the Suzuki coupling reaction (Chem. Rev., Vol. 95, No. 7, 2457 (1995), etc.), and this reaction can be carried out under conditions described in such reports.

Usually, the reaction is carried out under ambient pressure in an inert atmosphere of nitrogen, argon, helium, etc., and under pressure if needed. The reaction temperature is in the range of 15-300°C, preferably 30-200°C.

The reaction solvents may be water, aromatic hydrocarbons such as benzene, toluene, xylene, etc.; ethers such as 1,2-dimethoxyethane, diethyl ether, methyl t-butyl ether, tetrahydrofuran, dioxane, etc.; saturated hydrocarbons such as pentane, hexane, heptane, octane, cyclohexane, etc.; halogen compounds such as dichloromethane, chloroform, carbon tetrachloride, 1,2-dichloroethane, 1,1,1-trichloroethane, etc.; nitriles such as acetonitrile, benzonitrile, etc.; esters such as ethyl acetate, methyl acetate, butyl acetate, etc.; amides such as N,N-dimethylformamide, N,N-dimethylacetamide, N-methylpyrrolidone, etc.; or mixtures thereof. Of these, preferred are toluene, 1,2-dimethoxyethane, dioxane, and water. The amount of solvent used is usually 3-50 times, preferably 4-20 times by weight of the arylboronic acid or its derivatives.

The base used in the reaction may be, e.g., sodium carbonate, potassium carbonate, sodium hydroxide, potassium hydroxide, sodium bicarbonate, potassium bicarbonate, magnesium carbonate, lithium carbonate, potassium fluoride, cesium fluoride, cesium chloride, cesium bromide, cesium carbonate, potassium phosphate, methoxysodium, t-butoxypotassium*, t-butoxysodium*, t-butoxylithium*, etc., preferably sodium carbonate. The amount of such a base used is usually 0.7-10 molar equivalent, preferably 0.9-6 molar equivalent, with respect to the arylboronic acid or its derivatives.

The catalysts used in the reaction may be, e.g., palladium catalysts such as tetrakis(triphenylphosphine)palladium, dichlorobis(triphenylphosphine)palladium, dichloro[bis(diphenylphosphino)ethane]palladium, dichloro[bis(diphenylphosphino)propane]palladium, dichloro[bis(diphenylphosphino)butane]palladium, dichloro[bis(diphenylphosphino)ferrocene]palladium, etc.; nickel catalysts such as tetrakis(triphenylphosphine)nickel, dichlorobis(triphenylphosphine)nickel, dichloro[bis(diphenylphosphino)ethane]nickel, dichloro[bis(diphenylphosphino)propane]nickel, dichloro[bis(diphenylphosphino)butane]nickel, dichloro[bis(diphenylphosphino)ferrocene]nickel, etc., while tetrakis(triphenylphosphine)palladium is preferred. The amount of the catalyst used is

* [Butoxypotassium, etc., should possibly be "butylpotassium", etc.]

usually 0.001-1 molar equivalent, preferably 0.01-0.1 molar equivalent, with respect to the haloanthracene derivatives used.

The halogen in the haloanthracene derivatives may be, e.g., an iodine atom, bromine atom, chlorine atom, etc., preferably an iodine atom or bromine atom.

The halogenation agents used in the halogenation reaction may be, but not limited to, N-halosuccinimide. The amount of the halogenation agent used is usually 0.8-10 molar equivalent, preferably 1-5 molar equivalent, with respect to the anthracene derivatives.

The reaction is usually carried out in an inert solvent and in an inert atmosphere such as nitrogen, argon, helium, etc. The inert solvents that can be used are, e.g., N,N-dimethylformamide, N,N-dimethylacetamide, N-methylpyrrolidone, dimethyl sulfoxides, carbon tetrachloride, chlorobenzene, dichlorobenzene, nitrobenzene, toluene, xylene, methyl Cellosolve, ethyl Cellosolve, water, etc., preferably N,N-dimethylformamide and N-methylpyrrolidone. The amount of the solvents used is usually 3-50 times, preferably 5-20 times by weight of the anthracene derivatives. The reaction temperature is usually 0-200 °C, preferably 20-120 °C.

The boration reaction may be carried out in the usual manner (Nippon Kagakukai: Jikken Kagaku Goza, 4th ed., Vol. 24, pp. 61-90; J. Org. Chem., Vol. 60, 7508 (1995), etc.) For example, in the case of the reaction through the thiolation or Grignard reaction of haloanthracene derivatives, the reaction is usually carried out in an inert atmosphere such as nitrogen, argon, helium, etc., and in an inert solvent, e.g., saturated hydrocarbons such as pentane, hexane, heptane, octane, cyclohexane, etc.; ethers such as 1,2-dimethoxyethane, diethyl ether, methyl t-butyl ether, tetrahydrofuran, dioxane, etc.; aromatic hydrocarbons such as benzene, toluene, xylene, etc., or mixtures thereof, preferably diethyl ether and toluene. The amount of solvents used is usually 3-50 times, preferably 4-20 times the haloanthracene derivatives by weight.


The lithiation agents may be, e.g., alkylmetal reagents such as n-butyllithium, t-butyllithium, phenyllithium, methyllithium, etc.; amide bases such as lithium diisopropylamide, lithium bistrimethylsilylamide, etc., preferably n-butyllithium. The Grignard reagents can be prepared by reacting haloanthracene derivatives with metallic magnesium. The trialkyl borates that can be used as boration agents are, e.g., trimethyl borate, triethyl borate, triisopropyl borate, tributyl borate, etc., preferably trimethyl borate and triisopropyl borate.

Usually, the amounts of the lithiation agents and metallic magnesium used are, respectively, 1-10 molar equivalent, preferably 1-2 molar equivalent with respect to the haloanthracene derivatives. The amount of trialkyl borate used is usually 1-10 molar equivalent, preferably 1-5 molar equivalent, with respect to the haloanthracene derivatives. The reaction temperature is usually -100 to 50 °C, preferably -75 to 10 °C.

In the organic EL devices of the present invention, preferably, the luminescence layer contains anthracene derivatives represented by general formula (1) or (2), as the main component.

Furthermore, in the organic EL devices of the present invention, preferably, the luminescence layer contains also an arylamine compound and/or styrylamine compound.


The styrylamine compounds are preferably those represented by general formula (A) shown below:



(In the formula, Ar₂ is a group chosen from a phenyl group, biphenyl group, terphenyl group, stilbene group, or distyrylaryl group; Ar₃ and Ar₄ independently represent a hydrogen atom or C₆₋₂₀ aromatic group; Ar₂, Ar₃, and Ar₄ may be substituted. The p is a whole number of 1-4. Further preferably, at least one of Ar₃ and Ar₄ is substituted by a styryl group.)

Here, the C₆₋₂₀ aromatic group may be phenyl group, naphthyl group, anthranil group, phenanthryl group, terphenyl group, etc.

Arylamine compounds are preferably those represented by general formula (B) shown below:



(In formula, Ar₅-Ar₇ are (un)substituted aryl groups of 5-40 nuclear carbon atoms; q is a whole number of 1-4.)

The aryl groups of 5-40 nuclear carbon atoms are, e.g., the phenyl group, naphthyl group, anthranil group, phenanthryl group, pyrenyl group, koroniru [transliteration] group, biphenyl group, terphenyl group, pyrrolyl group, furanyl group, thiophenyl group, benzothiophenyl group, oxadiazolyl group, diphenylanthranil group, indolyl group, carbazolyl group, pyridyl group, benzoquinolyl, fluoranthenyl group, acenaphthofluoranthenyl group, stilbene group, etc.

Preferred substituents for such aryl groups are the C₁₋₆ alkyl group (ethyl group, methyl group, i-propyl group, n-propyl group, s-butyl group, t-butyl group, pentyl group, hexyl group, cyclopentyl group, cyclohexyl group, etc.), C₁₋₆ alkoxy group (ethoxy group, methoxy group, i-propoxy group, n-propoxy group, s-butoxy group, t-butoxy group, pentoxy group, hexyloxy group, cyclopentoxy group, cyclohexyloxy group, etc.), aryl group of 5-40 nuclear atoms, amino group substituted by an aryl group of 5-40 nuclear atoms, ester group having an aryl group of 5-40 nuclear atoms, ester group having a C₁₋₆ alkyl group, cyano group, nitro group, halogen atom, etc.

Next, the constitution of the organic EL devices of the present invention is explained.

Main constitutions of the organic EL devices of the present invention are:

- (1) Positive electrode/luminescence layer/negative electrode
- (2) Positive electrode/positive hole injection layer/luminescence layer/negative electrode
- (3) Positive electrode/luminescence layer/electron injection layer/negative electrode
- (4) Positive electrode/positive hole injection layer/luminescence layer/electron injection layer/negative electrode
- (5) Positive electrode/organic semiconductor layer/luminescence layer/negative electrode
- (6) Positive electrode/organic semiconductor layer/electron barrier layer/luminescence layer/negative electrode
- (7) Positive electrode/organic semiconductor layer/luminescence layer/adhesion improving layer/negative electrode
- (8) Positive electrode/positive hole injection layer/positive hole transport layer/luminescence layer/electron injection layer/negative electrode
- (9) Positive electrode/insulation layer/luminescence layer/insulation layer/negative electrode
- (10) Positive electrode/inorganic semiconductor layer/insulation layer/luminescence layer/insulation layer/negative electrode
- (11) Positive electrode/organic semiconductor layer/insulation layer/luminescence layer/insulation layer/negative electrode
- (12) Positive electrode/insulation layer/positive hole injection layer/positive hole transport layer/luminescence layer/insulation layer/negative electrode
- (13) Positive electrode/insulation layer/positive hole injection layer/positive hole transport layer/luminescence layer/electron injection layer/negative electrode, etc.

Of these, the constitution (8) is preferably used, but one is not limited to it.

Such organic EL devices are usually prepared on a transparent substrate. Such a transparent substrate is a base supporting the organic EL device and should have a light transmittance above 50% for visible light in 400-700 nm range; a smooth substrate is further preferred.

Such transparent substrates are preferably glass plates and synthetic resin plates. Glass plates may be especially soda ash glass, glass containing barium and strontium, lead glass, aluminosilicate glass, borosilicate glass, barium borosilicate glass, quartz, etc. Synthetic resin plates may be plates made from polycarbonate resins, acrylic resins, polyethylene terephthalate resin, polyether sulfide resins, polysulfone resins, etc.

The positive electrode should be made from high-work-function (above 4 eV) metals, alloys, electrically conductive compounds, or mixtures thereof. Specific examples of such electrode materials are metals such as Au, etc., and electrically conductive material such as CuI, ITO (indium tin oxide), SnO₂, ZnO, In-Zn-O, etc. Such a positive electrode can be formed by

the thin film process by vapor deposition, sputtering, etc., of the electrode materials. When the light emitted from the luminescence layer is taken from the positive electrode, the positive electrode should have a light transmittance above 10%. The positive electrode sheet resistance should be below several hundreds of Ω/\square . Furthermore, depending on the type of materials, usually, the positive electrode has a thickness of 10 nm~1 μm , preferably 10-200 nm.

Next, the negative electrode should be made from low-work-function (below 4 eV) metals, alloys, electrically conductive compounds, and mixtures thereof. Specific examples of such electrode materials include sodium, sodium-potassium alloy, magnesium, lithium, magnesium-silver alloy, aluminum/aluminum oxide, Al/Li₂O, Al/Li₂O, Al/LiF, aluminum-lithium alloy, indium, rare earth metals, etc.

Such a negative electrode can be formed by the thin film process by vapor deposition, sputtering, etc., of the electrode materials.

When the light emitted from the luminescence layer is taken from the negative electrode, the negative electrode should have a light transmittance above 10%. The negative electrode sheet resistance should be below several hundreds of Ω/\square . Furthermore, usually, the negative electrode has a thickness of 10 nm~1 μm , preferably 10-200 nm.

In the organic EL devices of the present invention, preferably a chalcogenide layer, metal halide layer, or metal oxide layer (hereafter, called surface layer in some cases) is formed on the surface of at least one of the pair of electrodes prepared. More specifically, a chalcogenide (including oxide) layer of a metal such as silicon, aluminum, etc., is formed on the positive electrode surface at the luminescence layer side, and a metal halide layer or metal oxide layer being formed on the negative electrode surface at the luminescence layer side. By doing this, the operation can be stabilized.

The chalcogenides are preferably SiO_x ($1 \leq x < 2$), AlO_x ($1 \leq x \leq 1.5$), SiON, SiAlON, etc. Metal halides may be LiF, MgF₂, CaF₂, rare earth metal fluorides, etc. Metal oxides may be Cs₂O, Li₂O, MgO, SrO, BaO, CaO, etc.

In the organic EL devices of the present invention, it is also preferred that a mixed area of an electron conducting compound and reductive dopant or a mixed area of a positive hole conducting compound and oxidative dopant is installed on the surface of at least one of the pair of electrodes prepared above. By doing this, the electron conducting compound is reduced to an anion, making the mixed area easier to inject and to conduct electrons to the luminescence layer. The positive hole conducting compound is oxidized to a cation, making the mixed area easier to inject and to conduct the positive holes to the luminescence layer. Preferred oxidative dopants are various Lewis acids and acceptor compounds. Preferred reductive dopants are alkali metals, alkali metal compounds, alkaline earth metals, rare earth metals, and compounds thereof.

In the organic EL devices of the present invention, the luminescence layer has:

- (1) an injection function: capable of injecting positive holes from the positive electrode or positive hole injection layer in the presence of an electric field;
- (2) a transport function: capable of moving the injected charge (electron and positive hole) by the force of the electric field;
- (3) a luminescence function: providing a field of recombination of the electron and positive hole, leading to light emission.

Such a luminescence layer can be formed by known methods such as vapor deposition, spin coating, LB process, etc. Molecular deposition films are especially preferred for the luminescence layer. Such molecular deposition films may be thin films deposited from gas-phase compounds or films formed by solidification of compounds in the solution or liquid state. Usually, such molecular deposition films are different from thin films formed by the LB process (molecular accumulation films) in an aggregate structure or high-order structure, and with respect to functions caused by such differences.

As disclosed in Japanese Kokai Patent No. SHO 57[1982]-51781, the luminescence layer can also be formed by forming thin films by the spin coating, etc., of a solution containing binders such as resins, etc., and the [luminescent] material compounds.

In the present invention, within the scope of the present invention, if desired, the luminescence layer may also contain known luminescence materials other than those of the present invention. Furthermore, the luminescence layer containing the luminescent material of the present invention may be laminated with a luminescent layer containing other known luminescent material.

The positive hole injection-transport layer aids positive hole injection into the luminescence layer and transports it to the luminescence region; the positive hole mobility is high and the ionization energy is small, below 5.5 eV. For such a positive hole injection-transport layer, materials capable of transporting the positive hole to the luminescent layer at a low electric field strength are needed. For example, preferred material should have at least 10^{-6} cm²/V-sec of positive hole mobility at an electric field of $10^4 \sim 10^6$ V/cm. Such materials can be selected from those commonly used as positive charge transport materials in light conducting materials and those used in positive hole injection layers of organic EL devices.

Such a positive hole injection-transport layer may be formed by the thin film process by the usual methods such as vacuum vapor deposition, spin coating, casting, LB process, etc. of the positive hole injection-transport materials. The film thickness of the positive hole injection-transport layer is usually, but not limited to, 5 nm-5 μ m.

The electron injection-transport layer aids the injection of electrons into the luminescence layer and transports it to the luminescence region, with electron mobility being high. The adhesion improving layer is made of a material having an especially good adhesion to the

negative electrode in the electron injection layer. Materials used in the electron injection layer are preferably metal complexes of 8-hydroxyquinoline or its derivatives. Specific examples of the metal complexes of 8-hydroxyquinoline or its derivatives include metal chelate oxinoid compounds containing a chelate of oxine (in general, 8-quinolinol or 8-hydroxyquinoline). For example, tris(8-quinolinol)aluminum can be used for the electron injection material.

Furthermore, in general, with the application of an electric field to ultra-thin films, pixel defects are easily formed by leaking and short [circuit]. To prevent this, a thin insulation film layer can be inserted between the electrodes.

The materials used for the insulation layer are, e.g., aluminum oxide, lithium fluoride, lithium oxide, cesium fluoride, cesium oxide, magnesium oxide, magnesium fluoride, calcium oxide, calcium fluoride, aluminum nitride, titanium oxide, silicon oxide, germanium oxide, silicon nitride, boron nitride, molybdenum oxide, ruthenium oxide, vanadium oxide, etc., mixtures, and laminates thereof.

The organic EL devices of the present invention may be prepared using such materials by methods described above by forming a positive electrode, luminescence layer, positive hole injection layer if needed, electron injection layer if needed, and finally a negative electrode. Organic EL devices can also be prepared in reverse order from the negative electrode to the positive electrode.

Next, an example of making an organic EL device with the installation of a positive electrode/positive hole injection layer/luminescence layer/electron injection layer/negative electrode, in that order, on a transparent substrate is explained.

First, vapor deposition or the sputtering process is used for forming a thin film from positive electrode material to a thickness below 1 μm , preferably 10-200 nm, on an appropriate transparent substrate. Next, a positive hole injection layer is installed on the positive electrode. The positive injection layer can be formed by vacuum vapor deposition, spin coating, casting, LB process, etc., as described above, while the vacuum vapor deposition process is preferred for the ease of obtaining uniform films and no pinholes. In forming a positive hole injection layer by the vacuum vapor deposition process, the vapor deposition conditions may vary according to the compounds used (positive hole injection layer material), crystal structure, and recombination structure of the desired positive hole injection layer, etc. In general, the vapor deposition source temperature is 50-450°C, vacuum is 10^{-7} ~ 10^{-3} torr, vapor deposition rate is 0.01-50 nm/sec, substrate temperature is -50 to 300°C, and film thickness is 5 nm-5 μm .

Next, the luminescence layer is installed on the positive hole injection layer. Also, this luminescence layer can be formed using the luminescent materials of the present invention by vacuum vapor deposition, sputtering, spin coating, casting, etc., for forming the luminescent material into a thin film, while the vacuum vapor deposition process is preferred for the ease of

uniform film formation and no pinhole formation. The vapor deposition conditions for forming a luminescent layer by vacuum vapor deposition may vary according to the compounds used, while they can be selected from conditions similar to those of the positive hole injection layer formation. The film thickness should be in the 10-40 nm range.

Next, an electron injection layer is installed on the luminescent layer. Also, in this case, similarly as in the positive hole injection layer and luminescent layer, the vacuum vapor deposition process is preferred for obtaining uniform films. Vapor deposition conditions can be selected from those used for the positive hole injection layer and luminescent layer.

Finally, lamination of the negative electrode produces an organic EL device. The metal negative electrode can be formed by vapor deposition or sputtering. However, the vacuum vapor deposition process is preferred for protection of the underlying organic layer from damage during film formation.

It is preferred that such organic EL devices are prepared at once from the positive electrode to negative electrode with one vacuum operation.

With dc-voltage application to this organic EL device, positive electrode +, and negative electrode -, light emission is observed at a voltage of 3-40 V. When voltage is applied at reverse polarity, current does not flow, with no light emission at all. Furthermore, when an ac voltage is applied, only with polarity of positive electrode + and negative electrode -, uniform light emission is observed. In this case, the ac applied may be in any wave form.

Next, the present invention is explained in further detail with examples. However, the present invention is not limited to such examples.

Synthesis Example 1

Synthesis of 10-(2-naphthyl)anthracene-9-boronic acid

In a 20-L flask under an Ar atmosphere, a solution of 549 g of 2-naphthaleneboronic acid (product of Tokyo Kasei Co.), 684 g of 9-bromoanthracene (product of Tokyo Kasei Co.), 61.5 g of tetrakis(triphenylphosphine)palladium(0) (product of Tokyo Kasei Co.), 4.9 L of toluene (product of Hiroshima Wako Co.), and 845.9 g of sodium carbonate (product of Hiroshima Wako Co.) in 4.9 L of water was heated under stirring under reflux for 24 h, allowed to cool to room temperature, and the crystals precipitated were filtered out and recrystallized from toluene to obtain 751 g of crystals.

In a 20-L flask under an Ar atmosphere, a mixture of 588 g of the above crystals, 4.5 L of dehydrated ether (product of Hiroshima Wako Co.), and 4.5 L of dehydrated toluene (product of Hiroshima Wako Co.) was cooled to -64°C using dry ice, treated over a period of 30 min with 1.2 L of 1.6M butyllithium/hexane solution (product of Hiroshima Wako Co.), allowed to react at -64°C for 2 h, treated over a period of 20 min with 866 g of triisopropyl boronate (product of

Tokyo Kasei Co.), allowed to return to room temperature, stirred for 12 h, cooled with ice, treated with 4 L of 2N hydrochloric acid at a temperature below 10°C, and treated with 1 L of toluene, followed by liquid separation, drying over sodium sulfate, concentration in vacuo, addition of hexane, and filtering out the crystals precipitated. The product was dissolved in 5 L of THF (tetrahydrofuran), treated with 500 mL of concentrated hydrochloric acid and 5 g of tetrabutylammonium bromide, stirred for 12 h, and filtered. The filtered crystals were dried to obtain 431 g of crystals.

The FD-MS (field desorption mass analysis) of this compound gave $m/z = 348$ to $C_{24}H_{17}BO_2 = 348$, confirming this compound as 10-(2-naphthyl)anthracene-9-boronic acid (yield: 47%).

Synthesis Example 2

Synthesis of 2-(4-bromophenyl)naphthalene

In a 300 mL-flask under an Ar atmosphere, a solution of 7.1 g of 2-naphthaleneboronic acid (product of Tokyo Kasei Co.), 12.9 g of 4-iodobromobenzene (product of Tokyo Kasei Co.), 0.6 g of tetrakis(triphenylphosphine)palladium(0) (product of Tokyo Kasei Co.), and 12.7 g of sodium carbonate (product of Hiroshima Wako Co.) in 60 mL of water was heated under reflux under stirring for 24 h, allowed to cool to room temperature, and filtered. The crystals filtered were recrystallized from toluene to obtain 9.0 g of crystals.

The FD-MS of this compound gave $m/z = 284, 282$ to $C_{16}H_{11}Br = 283$, confirming the product as 2-(4-bromophenyl)naphthalene (yield: 77%).

Synthesis Example 3

Synthesis of 3-(4-bromophenyl)fluoranthene

In a 500-mL flask under an Ar atmosphere, a mixture of 62 g of fluoranthene and 250 mL of DMF (product of Hiroshima Wako Co.) was heated to 80°C for dissolution, treated with 60 g of N-bromosuccinimide (product of Hiroshima Wako Co.) at 50°C, stirred for 2 h, treated with 500 mL of purified water, and the crystals precipitated were filtered out and purified by column chromatography to obtain 10.5 g of crystals.

In a 500-mL flask under an Ar atmosphere, a mixture of 10.0 g of the above crystals, 120 mL of dehydrated ether (product of Hiroshima Wako Co.) and 120 mL of dehydrated toluene (product of Hiroshima Wako Co.) was cooled to -64°C using dry ice, treated over a period of 30 min with 25 mL of 1.6 M butyllithium/hexane solution (product of Hiroshima Wako Co.), allowed to react at -64°C for 2 h, treated with 8 g of tiisopropyl brononate (product of Tokyo Kasei Co.) over a period of 20 min, allowed to return to room temperature, stirred for 12 h, cooled with ice, treated with 100 mL of 2N hydrochloric acid at a temperature below 10°C, and

treated with 25 mL of toluene, followed by phase separation, drying over sodium sulfate, concentration in vacuo, addition of hexane, and filtering the crystals precipitated. The filtered crystals were dissolved in 120 mL of THF, treated with 15 mL of concentrated hydrochloric acid and 0.15 g of tetrabutylammonium bromide, stirred for 12 h, and the crystals precipitated were filtered out and dried to obtain 7.0 g of 3-fluorantheneboronic acid crystals.

In a 300-mL flask under an Ar atmosphere, a solution of 7.0 g of the above crystals (product of Tokyo Kasei Co.), 9.0 g of 4-iodobromobenzene (product of Tokyo Kasei Co.), 0.6 g of tetrakis(triphenylphosphine)palladium(0) (product of Tokyo Kasei Co.), and 12.7 g of sodium carbonate (product of Hiroshima Wako Co.) in 60 mL of water was heated under reflux under stirring for 24 h, allowed to cool to room temperature, and the crystals precipitated were filtered out and recrystallized from toluene to obtain 6.4 g of crystals.

The FD-MS of this compound gave $m/z = 358$ to $C_{22}H_{15}Br = 357$, confirming this compound as 3-(4-bromophenyl)fluoranthene (yield: 6%).

Synthesis Example 4

Synthesis of 10-(3-fluoranthenyl)anthracene-9-boronic acid

In a 300-mL flask under an Ar atmosphere, a solution of 7.85 g of 3-fluorantheneboronic acid, 6.84 g of 9-bromoanthracene (product of Tokyo Kasei Co.), 0.6 g of tetrakis(triphenylphosphine)palladium(0) (product of Tokyo Kasei Co.), 50 mL of toluene, and 8.5 g of sodium carbonate (product of Hiroshima Wako Co.) in 50 mL of water was heated under reflux under stirring for 24 h, allowed to cool to room temperature, and the crystals precipitated were filtered out and recrystallized from toluene to obtain 4.6 g of crystals.

In a 300-mL flask under an Ar atmosphere, a mixture of 4.5 g of the above crystals and 100 mL of dehydrated DMF (product of Hiroshima Wako Co.) was heated to 80°C for dissolution, treated with 2.3 g of N-bromosuccinimide (product of Hiroshima Wako Co.) at 50°C, stirred for 2 h, treated with 200 mL of purified water, and the crystals precipitated were filtered out and recrystallized from toluene to obtain 4.5 g of crystals.

In a 300-mL flask under Ar atmosphere, a mixture of 4.5 g of the above crystals, 50 mL of dehydrated ether (product of Hiroshima Wako Co.) and 50 mL of dehydrated toluene (product of Hiroshima Wako Co.) was cooled to -64°C with dry ice, treated dropwise with 7 mL of 1.6M butyllithium/hexane solution (product of Hiroshima Wako Co.) over a period of 30 min, allowed to react at -64°C for 2 h, treated dropwise with 5.6 g of triisopropyl boronate (product of Tokyo Kasei Co.) over a period of 20 min, allowed to return to room temperature, stirred for 12 h, cooled with ice, treated with 40 mL of 2N hydrochloric acid at a temperature below 10°C, and treated with 10 mL of toluene. After phase separation, the toluene solution was dried over sodium sulfate, concentrated in vacuo, treated with hexane, and the crystals precipitated were

filtered out, dissolved in 50 mL of THF, treated with 5 mL of concentrated hydrochloric acid and 0.1 g of tetrabutylammonium bromide, stirred for 12 h, and the crystals precipitated were filtered out and dried to obtain 3.6 g of crystals.

The FD-MS of this compound gave $m/z = 422$ to $C_{30}H_{19}BO_2 = 422$, confirming this compound as 10-(3-fluoranthenyl)anthracene-9-boronic acid (yield: 32%).

Synthesis Example 5

Synthesis of 1-(4-bromophenyl)naphthalene

Synthesis Example 2 was repeated using 1-naphthaleneboronic acid in place of 2-naphthaleneboronic acid to obtain 29.9 g of colorless oil.

The FD-MS of this compound gave $m/z = 284, 282$ to $C_{16}H_{11}Br = 283$, confirming this compound as 1-(4-bromophenyl)naphthalene (yield: 88%).

Synthesis Example 6

Synthesis of 2-(3-bromophenyl)naphthalene

Synthesis Example 2 was repeated using 3-iodobromobenzene in place of 4-iodobromobenzene to obtain 20.1 g of colorless oil.

The FD-MS of this compound gave $m/z = 284, 282$ to $C_{16}H_{11}Br = 283$, confirming this compound as 1-(3-bromophenyl)naphthalene (yield: 75%).

Application Example 1

Synthesis of compound (AN8)

In a 300-mL flask under an Ar atmosphere, a solution of 5.98 g of the 10-(2-naphthyl)anthracene-9-boronic acid obtained in Synthesis Example 1, 4.05 g of 2-(4-bromophenyl)naphthalene obtained in Synthesis Example 2, 0.33 g of tetrakis(triphenylphosphine)palladium(0) (product of Tokyo Kasei Co.), 60 mL of 1,2-dimethoxyethane (product of Hiroshima Wako Co.), and 4.55 g of sodium carbonate (product of Hiroshima Wako Co.) in 21 mL of water was heated under reflux under stirring for 24 h, allowed to cool to room temperature, and the crystals precipitated were filtered out and purified by column chromatography to obtain 3.4 g of light yellow solid.

The FD-MS of this compound gave $m/z = 506$ to $C_{40}H_{26} = 506$, confirming this compound as AN8 (yield: 47%).

Application Example 2

Synthesis of compound (AN10)

In a 300-mL flask under an Ar atmosphere, a solution of 5.98 g of the 10-(2-naphthyl)anthracene-9-boronic acid obtained in Synthesis Example 1, 5.13 g of 3-(4-bromophenyl)fluoranthene obtained in Synthesis Example 3, 0.33 g of tetrakis(triphenylphosphine)palladium(0) (product of Tokyo Kasei Co.), 60 mL of 1,2-dimethoxyethane, and 4.55 g of sodium carbonate (product of Hiroshima Wako Co.) in 21 mL of water was heated under reflux under stirring for 24 h, allowed to cool to room temperature, and the crystals precipitated were filtered out and purified by column chromatography to obtain 3.3 g of light yellow solid.

The FD-MS of this compound gave $m/z = 580$ to $C_{46}H_{28} = 580$, confirming this compound as AN10 (yield: 40%).

Application Example 3

Synthesis of compound (AN28)

In a 300-mL flask under an Ar atmosphere, a solution of 7.24 g of the 10-(3-fluoranthenyl)anthracene-9-boronic acid obtained in Synthesis Example 4, 4.05 g of the 2-(4-bromophenyl)naphthalene obtained in Synthesis Example 2, 0.33 g of tetrakis(triphenylphosphine)palladium(0) (product of Tokyo Kasei Co.), 60 mL of 1,2-dimethoxyethane (product of Hiroshima Wako Co.), and 4.55 g of sodium carbonate (Hiroshima Wako Co.) in 21 mL of water was heated under reflux under stirring for 24 h, allowed to cool to room temperature, and the crystals precipitated were filtered out and purified by column chromatography to obtain 3.6 g of light yellow solid.

The FD-MS of this compound gave $m/z = 580$ to $C_{46}H_{28} = 580$, confirming this compound as AN28 (yield: 43%).

Application Example 4

Synthesis of compound (AN30)

In a 300-mL flask under an Ar atmosphere, a solution of 7.24 g of the 10-(3-fluoranthenyl)anthracene-9-boronic acid obtained in Synthesis Example 4, 5.13 g of the 3-(4-bromophenyl)fluoranthene obtained in Synthesis Example 3, 0.33 g of tetrakis(triphenylphosphine)palladium(0) (product of Tokyo Kasei Co.), 60 mL of 1,2-dimethoxyethane (product of Hiroshima Wako Co.), and 4.55 g of sodium carbonate (Hiroshima Wako Co.) in 21 mL of water was heated under reflux under stirring for 24 h, allowed to cool to room temperature, and the crystals precipitated were filtered out and purified by column chromatography to obtain 3.1 g of a light yellow solid.


The FD-MS of this compound gave $m/z = 654$ to $C_{52}H_{30} = 654$, confirming this compound as AN30 (yield: 33%).

Application Example 5


Manufacture of organic EL device

An ITO transparent electrode-fitted glass substrate (product of Diomatic Co.) of 25 mm x 75 mm x 1.1 mm (thickness) was cleaned by ultrasonic waves in isopropyl alcohol for 5 min, then by UV-ozone for 30 min. The cleaned transparent electrode line-fitted glass substrate was loaded in the substrate holder of a vacuum vapor deposition device. A 60-nm-thick N,N'-bis(N,N'-diphenyl-4-aminophenyl)-N,N-diphenyl-4,4'-diamino-1,1'-biphenyl film (hereafter referred to as TPD232 film) was formed on the transparent electrode side, covering the transparent electrode. This TPD232 film is the positive hole injection layer. A 20-nm-thick N,N,N',N'-tetra(4-biphenyl)-diaminobiphenylene film (hereafter referred to TBDB) was then formed on the TPD232 film. This film is the positive hole transport layer. A 40-nm-thick (AN8) film was formed as luminescent material on the TBDB film by vapor deposition. At the same time, the styryl-group-containing amine compound (D1) was vapor-deposited as luminescent material at AN8:D1 = 40:2 by weight. This film functions as the luminescent layer. A 10-nm-thick Alq film was then formed on the above film. This functions as an electron injection layer. Binary vapor deposition of the reductive dopant Li (Li source: product of Saes Target Co.) and Alq produced an Alq:Li film (film thickness: 10 nm) as an electron injection layer (negative electrode). Metallic Al was vapor deposited on the Alq:Li film to form a metallic negative electrode to obtain an organic EL device.


The organic EL device obtained was measured for luminescence efficiency and half-life under normal use at an initial brightness of 1000nit. Results are given in Table 1.




TPD232



TBDB



D 1



Alq

Application Examples 6-8


Manufacture of organic EL devices

Application Example 5 was repeated using the luminescent materials given in Table 1 in place of AN8 to obtain organic EL devices, which were measured for luminescence efficiency and half-life under normal use at an initial brightness of 1000nit. Results are given in Table 1.

Application Example 9

Manufacture of organic EL device

Application Example 5 was repeated using the aromatic amine (D2) in place of the styryl-group-containing amine compound (D1) to obtain an organic EL device, which was then measured for luminescence efficiency and half-life under normal use at an initial brightness of 1000nit. Results are given in Table 1.



Application Example 10

Synthesis of compound (AN5)

Application Example 1 was repeated using 3,5-diphenylbromobenzene in place of 2-(4-bromophenyl)naphthalene to obtain 5.6 g of light yellow solid.

The FD-MS of this compound gave $m/z = 532$ to $C_{42}H_{28}Br = 532$, confirming this compound as AN5 (yield: 45%).

Application Example 11

Synthesis of compound (AN7)

Application Example 1 was repeated using 1-(4-bromophenyl)naphthalene in place of 2-(4-bromophenyl)naphthalene to obtain 7.8 g of a light yellow solid.

The FD-MS of this compound gave $m/z = 506$ to $C_{40}H_{26}Br = 506$, confirming this compound as AN7 (yield: 54%).

Application Example 12

Synthesis of compound (AN49)

Application Example 1 was repeated using 2-(3-bromophenyl)naphthalene in place of 2-(4-bromophenyl)naphthalene to obtain 6.9 g of light yellow solid.

The FD-MS of this compound gave $m/z = 506$ to $C_{40}H_{26}Br = 506$, confirming this compound as AN7 (yield: 52%).

Application Examples 13-15

Manufacture of organic EL devices


Application Example 5 was repeated using luminescent compounds described in Table 1 in place of AN8 to obtain organic EL devices, which were then measured for luminescence

efficiency and half-life under normal use at an initial brightness of 1000nit. Results are given in Table 1.

Comparative Example 1

Manufacture of organic EL device

Application Example 5 was repeated using an1 as the luminescent material in place of AN8 to obtain an organic EL device, which was then measured for luminescence efficiency and half-life under normal use at an initial brightness of 1000nit. Results are given in Table 1.



Comparative Example 2

Manufacture of organic EL device

Application Example 5 was repeated using an2 as the luminescent material in place of AN8 to obtain an organic EL device, which was then measured for luminescence efficiency and half-life under normal use at an initial brightness of 1000nit. Results are given in Table 1.




Table 1

	Fluorescent layer compound	Luminescence efficiency	Half-life	Luminescence color
		(cd/A)	(hours)	
AA5	AN8/D1	11.2	4200	Blue
AA6	AN10/D1	11.0	4000	Blue
AA7	AN28/D1	10.9	3700	Blue
AA8	AN30/D1	10.8	3700	Blue
AA9	AN8/D2	10.6	3200	Blue
AA13	AN5/D1	11.0	2200	Blue
AA14	AN7/D1	11.3	4500	Blue
AA15	AN49/D1	11.3	4500	Blue
CC1	an/D1	9.0	2200	Blue
CC2	an2/D1	8.8	1100	Blue

AA: Application Example

CC: Comparative Example


As shown in Table 1, the organic EL devices of Application Examples 5-9 and 13-15 have a high luminescence efficiency and very long service life, while the organic EL devices of Comparative Example 1 and 2 have a low luminescence efficiency and short service life.

Industrial application possibilities


As explained in detail above, the organic EL devices of the present invention and the organic EL devices using the anthracene compounds of the present invention have a high luminescence efficiency and long service life, thus they are useful for organic EL devices expected for long-term continuous use.

Claims


1. Organic electroluminescence device having at least one luminescence-layer-containing organic thin film layer sandwiched between the anode and cathode, wherein at least one layer of the organic thin film layer contains the anthracene derivative represented by general formula (1) shown below, alone or as a component in a mixture:



(in the formula, Ar is an (un)substituted condensed aromatic group of 10-50 nuclear carbon atoms; Ar' is an (un)substituted aromatic group of 6-50 nuclear carbon atoms; X is an (un)substituted aromatic group of 6-50 nuclear carbon atoms, (un)substituted aromatic heterocyclic group of 5-50 nuclear carbon atoms, (un)substituted alkyl group of 1-50 carbon atoms, (un)substituted alkoxy group of 1-50 carbon atoms, (un)substituted aralkyl group of 6-50 carbon atoms, (un)substituted aryloxy group of 5-50 nuclear carbon atoms, (un)substituted arylthio group of 5-50 nuclear carbon atoms, (un)substituted alkoxycarbonyl group of 1-50 carbon atoms, carboxy group, halogen atom, cyano group, nitro group, or hydroxy group; a, b, and c are whole numbers of 0-4; and n is a whole number of 1-3; when n is 2 or more, the formula inside the parenthesis shown below may be the same or different:



2. The organic electroluminescence device described in Claim 1, wherein Ar in general formula (1) is selected from the general formulas given below:




(Ar₁ is an (un)substituted aromatic group of 6-50 nuclear carbon atoms.)

3. The organic electroluminescence device described in Claim 1, wherein the luminescence layer contains the anthracene derivative represented by general formula (1) as the main component.


4. The organic electroluminescence device described in Claim 1, wherein the luminescence layer further contains an arylamine compound.

5. The organic electroluminescence device described in Claim 1, wherein the luminescence layer further contains a styrylamine compound.

6. Anthracene derivative represented by general formula (2) shown below:




(in the formula, Ar is an (un)substituted condensed aromatic group of 10-50 nuclear carbon atoms; Ar' is an (un)substituted aromatic group of 6-50 nuclear carbon atoms; X is an (un)substituted aromatic group of 6-50 nuclear carbon atoms, (un)substituted aromatic heterocyclic group of 5-50 nuclear carbon atoms, (un)substituted alkyl group of 1-50 carbon atoms, (un)substituted alkoxy group of 1-50 carbon atoms, (un)substituted aralkyl group of 6-50 carbon atoms, (un)substituted aryloxy group of 5-50 nuclear carbon atoms, (un)substituted arylthio group of 5-50 nuclear carbon atoms, (un)substituted alkoxycarbonyl group of 1-50 carbon atoms, carboxy group, halogen atom, cyano group, nitro group, or hydroxy group; a, b, and c are whole numbers of 0-4; and n is a whole number of 1-3; when n is 2 or more, the formula inside the parenthesis shown below may be the same or different:



7. The anthracene derivative described in Claim 6, being material for an organic electroluminescence device.

8. Organic electroluminescence device having at least one luminescence-layer-containing organic thin film layer sandwiched between an anode and cathode, wherein at least one layer of the organic thin film layer contains the anthracene derivative represented by general formula (2) described in Claim 6, alone or as a component in a mixture.

9. The organic electroluminescence device described in Claim 8, wherein Ar in general formula (2) is selected from the general formulas given below:



(Ar₁ is an (un)substituted aromatic group of 6-50 nuclear carbon atoms.)

10. The organic electroluminescence device described in Claim 8, wherein the luminescence layer contains the anthracene derivative represented by general formula (2) as the main component.

11. The organic electroluminescence device described in Claim 8, wherein the luminescence layer further contains an arylamine compound.

12. The organic electroluminescence device described in Claim 8, wherein the luminescence layer further contains a styrylamine compound.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP03/10402

A. CLASSIFICATION OF SUBJECT MATTER

Int.Cl⁷ C09K11/06, H05B33/14, C07C13/66, C07C15/28

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

Int.Cl⁷ C09K11/06, H05B33/14, G03G5/06, C07C13/66, C07C15/28

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

CA (STN), REGISTRY (STN)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	JP 2002-329580 A (Canon Inc.), 15 November, 2002 (15.11.02), Claims; Par. No. [0083] (Family: none)	1, 3-8, 10-12
X A	WO 02/14244 A1 (Mitsui Chemicals, Inc.), 21 February, 2002 (21.02.02), & JP 2002-154993 A & EP 1221434 A1 & US 2003/0087126 A1	1, 3-8, 10-12 2, 9
X A	JP 2001-223082 A (Toray Industries, Inc.), 17 August, 2001 (17.08.01), Claims; Par. Nos. [0030] to [0036] (Family: none)	1, 3-8, 10-12 2, 9

☒ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such

combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search
11 November, 2003 (11.11.03)Date of mailing of the international search report
25 November, 2003 (25.11.03)Name and mailing address of the ISA/
Japanese Patent Office

Authorized officer

Facsimile No.

Telephone No.

Form PCT/ISA 210 (second sheet) (July 2009)

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP03/10402

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	US 2002/0048688 A1 (Idemitsu Kosan Co., Ltd.), 25 April, 2002 (25.04.02), Claims; page 6 & WO 01/076323 A1 & JP 2001-284050 A & EP 1191822 A1	1, 3-8, 10-12 2, 9
X Y	EP 1009044 A2 (EASTMAN KODAK CO.), 14 June, 2000 (14.06.00), & JP 2000-182776 A & US 2002/0028346 A1	1, 2, 6-9 3-5, 10-12
Y	JP 11-3782 A (Toppan Printing Co., Ltd.), 06 January, 1999 (06.01.99), Claims (Family: none)	3-5, 10-12
Y	JP 10-294179 A (Mitsubishi Chemical Corp.), 04 November, 1998 (04.11.98), Claims (Family: none)	3-5, 10-12
Y	WO 02/038524 A1 (Idemitsu Kosan Co., Ltd.), 16 May, 2002 (16.05.02), Claims & JP 2001-335516 A & EP 1333018 A1	3-5, 10-12

Form PCT/ISA/210 (continuation of second sheet) (July 1998)